



## Drill Results

San Gonzalo zone	Page 2
Elena Tolosa zone	Page 9
Aguila Mexicana area	Page 19
Churumbo zone	Page 20
Gap zone	Page 20
Guadalup vein	Page 22
La Estela vein	Page 22
Los Angeles zone	Page 23
Nuestra Seniora	Page 24
San Jose zone	Page 25
San Luis zone	Page 27
San Pedro & Paulo zones	Page 28
Santa Ana zone	Page 28
Santiago vein	Page 28





<b>SG-08-06</b> <i>Intersected San Gonzalo between 214.5 - 219.70m (5.65m) 0.88g/t Au, 235 g/t Ag</i>								
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	214.05	214.85	0.8	0.729	204	2944	21400	17600
San Gonzalo Vein With Sulphide Minerals	214.85	215.95	1.1	0.523	95	1189	5264	6417
	215.95	216.8	0.65	0.335	47.5	398	1486	2918
	216.8	218	1.2	0.36	87.3	1960	5342	7772
	218	218.85	0.85	<b>3.228</b>	<b>758.9</b>	3731	18500	19000
	218.85	219.7	0.85	0.402	<b>316.1</b>	7094	17500	14800

<b>SG-08-05</b> <i>Didn't intersect SG vein but hit breccia zone which may be part of another system</i>								
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	437.75	438.5	0.75	0.03	0.1	5	33	32
Breccia Zone	438.5	438.9	0.4	<0.005	<0.1	6	22	76
	438.9	439.55	0.65	0.015	<0.1	7	18	65
	439.55	440.35	0.8	0.01	<0.1	8	14	30

<b>SG-08-04</b> <i>Intersected San Gonzalo vein 261.25 - 264.6m (3.35m) 0.5 g/t Gold, 59 g/t Silver</i>								
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	261.25	261.75	0.5	0.802	81	145	754	1251
	261.75	262.75	1	0.331	61.4	234	1014	2002
San Gonzalo Vein	262.75	263.15	0.4	0.04	11.2	39	109	353
	263.15	263.7	0.55	0.99	85	119	396	794
	263.7	264.6	0.9	0.424	49.7	208	440	702

<b>SG-08-03</b> <i>Intersected SG Vein 322.2-325.7m (3.7m) 0.41 g/t Gold, 119 g/t Silver</i>								
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	321.04	322	0.6	0.016	1.6	33	126	423
Andesite volcanic with quartz veins	322	322.85	0.65	0.215	74.1	409	11500	2725
	322.85	323.7	0.85	0.195	75.2	389	2665	3405
	323.7	324.1	0.4	0.109	221	3668	65000	3569
	324.1	324.9	0.8	0.925	55	264	6449	3610
	324.9	325.7	0.8	0.457	223.5	729	15500	4012
	325.7	327	1.3	0.288	31.8	483	2241	2408

<b>SG-08-02</b> <i>Intersected 2 zones of mineralization 1.6m @ 1.72 g/t Au , 704 g/t Ag &amp; 3.0m</i>								
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	257.5	258.05	0.55	0.42	150.2	318	2832	5393
	258.05	258.7	0.65	3.84	1564.4	264	13100	13900
	258.7	259.1	0.4	0.075	68.1	79	266	502
	263.05	263.75	0.7	10.765	1275.6	7394	106000	146000
	263.75	263.95	0.2	0.115	62.3	364	4916	31000
	263.95	264.7	0.75	2.606	587.4	3427	76200	200000
	264.7	265.3	0.6	7.337	224.1	2363	146000	355000
	264.3	266.05	0.75	22.56	204.2	917	80000	126000

<b>SG-08-01</b> <i>Intersected a 2.75m zone @ 1.13 g/t gold and 155 g/t silver</i>								
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	143.05	144.4	1.35	1.33	168.6	309	530	3598
	144.4	145.8	1.4	0.93	142.1	131	560	1540



AVINO SILVER &  
GOLD MINES LTD.

2007 San Gonzalo zone drilling

Holes #1-40

<b>SG-07-40</b> <i>Bearing 230 - Dip 74 - Length 516.05m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
Santiago vein	33.2	33.7	0.5	5.966	2851.9	576	748	1558
Qtz veining w/chalcopyrite	255.65	256.75	1.1	0.03	212.6	6115	1386	2887
Quartz veinlet w/sulfides	275.9	276.45	0.55	0.059	390	978	17000	364
Quartz veinlet w/sulfides along cor	382.9	383.25	0.35	1.926	208.7	331	270	307
San Gonzalo vein	500.25	501.65	1.4	0.075	14.1	71	263	833
San Gonzalo vein	501.65	502.45	0.8	0.015	3.1	25	49	81

<b>SG-07-39</b> <i>Bearing 220 - Dip 73 - Length 128.05m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
San Gonzalo vein	76.5	77	0.5	0.286	25.5	61	943	918
San Gonzalo vein	77	77.8	0.8	0.192	66.5	118	324	357
San Gonzalo vein	77.8	78.6	0.8	0.082	58.5	142	1001	1032

<b>SG-07-38</b> <i>Bearing 221 - Dip 66.5 - Length 214.15m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
S Gonzalo Vein Ox-milky wh qtz vei	168.65	170	1.35	0.716	88.2	231	1278	2217

<b>SG-07-37</b> <i>Bearing 219 Dip 53 Length 154.35m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
San Gonzalo Vein	145.45	146.55	1.1	0.21	220.7	104	698	2554
San Gonzalo Vein	146.55	147.55	1	0.108	63.6	68	670	1257

<b>SG-07-36</b> <i>Bearing 215 - Dip 45 - Length 102.15m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
San Gonzalo vein	65.3	65.65	0.35	<0.005	6	13	60	520
Los Angeles vein	78.05	78.8	0.75	0.03	12.1	13	29	428
Silicif tuff	78.8	80.45	1.65	0.01	3.8	103	95	456
Los Angeles vein	80.45	81.95	1.5	0.105	19.5	73	144	281

<b>SG-07-34</b> <i>Bearing 215 - Dip 45 - Length 100m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
San Gonzalo vein	161.5	162.6	1.1	0.258	28	60	129	231
Silicif tuff	162.6	163.95	1.35	0.072	6.8	9	42	285
Quartz veining	163.95	165.02	1.1	0.05	7	26	43	220
Quartz veining	165.05	166.2	1.15	0.066	5.1	22	43	355
San Gonzalo vein	166.2	167.3	1.1	0.058	19.7	24	58	822

<b>SG-07-33</b> <i>Bearing 209 - Dip 45 - Length 130.6</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
San Gonzalo vein	116.15	117.15	1	0.283	0.01	361	8295	25100
San Gonzalo vein	117.15	118.4	1.25	0.337	0.01	659	7934	32900
San Gonzalo vein	118.4	119.55	1.15	0.934	0.03	475	10000	39300
San Gonzalo vein	119.55	120.55	0.95	0.168	0.005	193	2418	7965
San Gonzalo vein	120.5	121.85	1.35	1.996	0.06	878	31400	17400
San Gonzalo vein	121.85	122.7	0.85	0.378	0.01	954	17700	61800
San Gonzalo vein	122.7	123.6	0.9	0.115	0.003	192	1495	1573

<b>SG-07-32</b> <i>Bearing 215 - Dip 70 - Length 390.2m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
Hanging wall vein	392.5	393.2	0.7	2.149	192.8	5.62	1484	1153
Strong silicif and quartz veining	393.2	394.6	1.4	0.123	24.1	0.7	393	1081
Strong silicif and quartz veining	394.6	396.2	1.6	0.14	7.7	0.22	148	522
San Gonzalo vein system	396.2	397.75	1.55	0.419	65.9	0.92	528	919

<b>SG-07-31 Bearing 215 - Dip 70 - Length 71.85m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
San Gonzalo vein	51.25	51.7	0.45	1.085	449.3	294	1812	7272

<b>SG-07-30 Bearing 215 - Dip 64 - Length 158.4</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
Strong argillized rock+diss pyrite	79.4	80.25	0.85	0.605	213.8	3741	990	2370
Veinlets with sulfides	116.35	116.9	0.55	1.38	519.1	6162	18200	11600
Caliche zone	138.85	139.9	1.05	0.105	10.5	30	110	541
no core recovered between 139.9-	140.8	141.45	0.65	0.786	53.7	179	439	394

<b>SG-07-29 Bearing 215 - Dip 45 - Length 100m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
HW San Gonzalo vein	70.2	71.2	1	0.185	69.6	862	1956	5259
Wh qtz veining w/ strong pyrite	71.2	72.35	1.15	0.091	13.6	173	1151	2622
Wh qtz veining w/ strong pyrite	72.35	73.3	0.95	0.125	18.6	174	1242	2799
Silicified material	75.45	76.35	0.9	0.025	21	831	973	983
San Gonzalo vein	76.35	77.2	0.85	0.153	299.1	3456	218	2242
San Gonzalo vein	77.2	78	0.8	0.542	243.8	3774	4778	3515
San Gonzalo vein	78	78.9	0.9	0.185	207.1	563	3317	3559

<b>SG-07-28 Bearing 215 - Dip 73 - Length 319.5m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
San Gonzalo Vein	310.1	311.05	0.95	0.794	102.4	315	1695	3781

<b>SG-07-27 Bearing 215 - Dip 70 - Length 237.75m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
Qtz veinlet w/ diss sulfs	139.4	139.95	0.55	6.13	153.7	1298	13000	20900
San Gonzalo HW vein	206.45	207.4	0.95	0.986	100.1	410	1349	2824
San Gonzalo HW vein	207.4	207.8	0.4	2.272	754.1	252	2373	6703
San Gonzalo vein	217.15	217.55	0.4	0.711	60.7	166	260	949
Veinlet w/ base metal mineralizatio	227.65	228	0.35	1.644	94.7	6092	17400	65100
Host Rock Silicied tuff	233	233.65	0.65	0.122	57.5	3864	4459	3409
Wh qz vein	233.65	234.1	0.45	10.63	117.3	953	1424	1631

<b>SG-07-26 Bearing 215 - Dip 75 - Length 393.4m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
San Gonzalo Vein	381.55	382.45	0.9	0.015	11.3	187	375	1149
San Gonzalo Vein	382.45	383.15	0.7	0.175	22.7	101	492	2262
San Gonzalo Vein	383.15	383.85	0.7	0.378	59.7	194	1437	838

<b>SG-07-25 Bearing 215 - Dip 65 Length 190.45m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
Side Vein	103.95	104.2	0.25	0.165	209.2	920	5600	196
Side Vein	104.75	105.05	0.3	0.239	283.4	10800	3540	1450
Side Vein	133.35	133.65	0.3	1.517	79	950	39300	1180
San Gonzalo Footwall vein	175.85	176.75	0.9	1.096	343.2	11000	6100	2840
San Gonzalo vein	179.4	179.95	0.55	0.243	39.5	281	670	1500
San Gonzalo vein	179.95	180.85	0.9	0.123	12.1	48	91	700
San Gonzalo vein	180.85	181.7	0.85	0.541	61.5	50	66	560
San Gonzalo vein	181.7	182.8	1.1	0.851	62.6	67	135	640
San Gonzalo vein	182.8	183.3	0.5	1.396	113	128	209	780
San Gonzalo vein	183.3	184.25	0.95	2.88	368.8	197	780	1790

<b>SG-07-24 Bearing 215 - Dip 53 - Length 124.4m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
Side Vein	69.3	69.6	0.3	0.82	631.1	153	6500	6800
San Gonzalo vein	113.9	114.7	0.8	0.135	27.7	172	1530	5000
San Gonzalo vein	114.7	115.8	1.1	0.097	12.2	246	3230	7500
San Gonzalo vein	115.8	116.6	0.8	16.32	2804.4	227	1350	15600
San Gonzalo vein	116.6	117.25	0.65	10.491	5265.2	910	15200	28900
San Gonzalo vein	117.25	118.4	1.15	0.147	28.9	27	1040	2350
San Gonzalo vein	118.4	119.45	1.05	0.23	18.1	110	2110	2980

<b>SG-07-23 Bearing 215 - Dip 69 - Length 303.45m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
Silicified Tuff rock	293.8	294.5	0.7	0.425	254	114	820	1933
San Gonzalo vein	294.5	295.55	1.05	2.512	502.7	3059	11400	39800
San Gonzalo vein	295.55	296.1	0.55	1.408	63.1	131	412	3345
San Gonzalo vein	296.1	297.6	1.5	15.771	1511.8	2570	60600	42300
San Gonzalo vein	297.6	297.85	0.25	13.988	763.7	1328	30500	36900
San Gonzalo vein	297.85	298.75	0.9	0.214	56.3	144	437	732

<b>SG-07-22 Bearing 215 - dip 55 - Length 232.5m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
San Gonzalo vein	227.05	228.1	1.05	2.052	211.2	1277	6398	4162
San Gonzalo vein	228.1	229.25	1.15	0.868	109.2	165	487	690
San Gonzalo vein	229.25	229.75	0.5	1.778	126.7	199	859	1763

<b>SG-07-21 Bearing 033 - Dip 54 - Length 295m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
Wh qtz veining w/ diss fine sulfs	135	136.35	1.35	0.215	20.7	840	1168	8682
Silicified Tuff rock	280.05	280.6	0.55	0.04	4.7	11	459	699
San Gonzalo Vein	280.6	281.25	0.65	0.358	32	45	1884	5101
San Gonzalo Vein	281.6	282.35	0.75	0.209	35.3	184	778	4569
San Gonzalo Vein	282.35	283.5	1.15	2.172	24.9	127	444	1123
San Gonzalo Vein	283.5	284.1	0.6	1.37	59.2	521	7016	1299
San Gonzalo Vein	284.1	284.9	0.8	0.055	5.5	66	1043	975
San Gonzalo Vein	284.9	285.3	0.4	0.233	133.1	1056	24800	29000

<b>SG-07-20 Bearing 215 - Dip 66 - Length 247.4m</b>								
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm	
11.4	12.6	1.2	0.125	64.5	57	106	167	
12.6	13.25	0.65	0.419	648.8	534	1182	2124	
13.25	14.1	0.85	0.099	18.1	84	302	2080	
51.05	51.55	0.5	0.206	22.2	22	109	218	
53.45	54	0.55	2.454	839.2	536	5927	7122	
112.1	112.5	0.4	0.135	131.7	8533	756	413	
146.8	147.55	0.75	0.145	32.2	1568	382	830	
195.65	195.85	0.2	0.07	187.3	10700	240	1730	

<b>SG-07-19 Bearing - 252 - Dip 66 - Length 345.0m</b>								
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm	
126.4	129.9	0.5	94.421	265.7	25500	3379	1631	
131.2	131.5	0.3	1.385	68	18000	426	343	
133.85	134.6	0.75	1.011	27.3	5173	138	229	
229.05	229.7	0.65	0.21	10.1	58	1588	2154	
230.4	230.8	0.4	0.973	116.1	1237	1245	2821	
236.55	237.4	0.85	0.07	22.3	90	127	1560	
237.4	238.25	0.85	0.097	45	50	209	1581	
244.8	245.7	0.9	0.068	6.9	17	98	1406	
252.95	253.5	0.55	0.164	10.3	178	279	653	
253.5	254.65	1.15	0.04	39.4	1767	1096	814	

<b>SG-07-18</b> <i>Bearing 215 - Dip 66 - Length 238.05m</i>							
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
166.6	167.5	0.9	0.198	16.5	490	2612	4085
167.5	168.2	0.7	0.63	55	2035	2219	692
168.2	168.75	0.55	0.215	145.5	6887	835	302
171.15	171.4	0.25	0.454	132	5281	1611	3216
214.2	214.6	0.4	0.185	14.7	13	711	144
219.75	221	1.25	0.109	23.6	164	1334	2321
221	222.2	1.2	0.725	66	117	863	1836
222.2	223.4	1.2	0.01	5.3	113	136	473
232.65	233.35	0.7	0.01	4	72	71	981
233.35	234.1	0.75	1.369	112.8	126	1045	1571
234.1	234.9	0.8	0.485	66.7	305	1626	3523
234.9	235.8	0.9	0.015	46.8	1643	583	395
235.8	237	1.2	0.01	44.2	1678	443	274
237	238.05	1.05	0.02	9.7	370	222	373

  

<b>SG-07-17</b> <i>Bearing 251 - Dip 55 - Length 69.8m</i>							
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
46.7	47.6	0.9	0.054	15.5	82	1259	1801
47.6	48.2	0.6	0.02	5.2	84	2129	1270
53.05	53.95	0.9	0.055	7.1	53	1793	11300

  

<b>SG-07-16</b> <i>Bearing 215 - Dip 55 - Length 99.85m</i>							
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
48.6	49.05	0.45	6.171	1189	241	2844	7658
95.75	96.2	0.45	0.078	9.6	27	193	430
96.2	96.75	0.55	0.253	326.4	6489	3126	4661
96.75	97.55	0.8	0.159	19.2	483	336	752

  

<b>SG-07-15</b> <i>Bearing 215 - Dip 49 - Length 96.2m</i>							
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
32.25	33.2	0.95	0.063	20.8	67	93	4727
33.2	33.9	0.7	0.045	6.3	35	23	662
63.5	63.9	0.4	0.743	>200	104	2725	2998

  

<b>SG-07-14</b> <i>Bearing 053 - Dip 52 - Length 295.20m</i>							
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
287.6	288.5	0.9	2.356	179.1	727	1267	2755
288.5	289.05	0.55	0.427	55.3	188	381	1440
289.05	289.85	0.8	1.594	107.8	710	1386	4558
289.85	290.85	1	3.84	3623.2	2727	29300	48300
290.85	291.85	1	0.478	202.6	236	1796	3579
291.85	293	1.15	0.215	64.9	125	1096	1600

  

<b>SG-07-13</b> <i>Bearing 012 - Dip 49 - Length 158.6m</i>							
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
147.45	148.45	1	0.55	91.5	3199	2205	2436
148.45	149.05	0.6	0.155	77.9	326	724	7039
149.05	149.7	0.65	1.209	150.8	192	1284	1670
149.7	150.7	1	0.778	500.6	264	1.779	3037
150.7	151.5	0.8	3.153	238.9	1910	11000	10700
151.5	152.2	0.7	0.822	121.3	241	922	4552
152.2	153	0.8	1.057	44.5	91	783	1730

<b>SG-07-12</b> <i>Bearing 037 - Dip 45 - Length 106.6m</i>							
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
165.65	166.4	0.75	22.902	1609.9	840	2106	3692
166.4	167.05	0.65	8.366	898	262	974	2266
167.05	67.75	0.7	13.508	427.6	261	1188	1282
167.75	168.55	0.8	1.89	283.6	1169	9356	4652
168.55	169.45	0.9	2.792	194.4	293	427	723

<b>SG-07-11</b> <i>Bearing 012 - Dip 52 - Length 158.6m</i>							
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
146.75	147.45	0.7	0.676	40	1488	13100	14200
147.45	148.15	0.7	0.21	21	379	5831	12900
148.15	149.15	1	1.86	66.6	61	439	1206
149.15	150	0.85	1.331	222.4	451	3627	6933

<b>SG-07-10</b> <i>Bearing 046 - Dip 58 - Length 162.9m</i>							
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
154.3	154.65	0.35	5.143	992.3	756	2793	5026
154.65	155.25	0.6	0.381	27.5	102	657	923
155.25	155.9	0.65	0.667	130.2	154	729	1010
155.9	156.8	0.9	2.914	291.8	190	797	1757
156.8	157.55	0.75	4.183	926.8	1015	2995	3153
157.55	158.05	0.5	4.114	575.9	671	1486	1947

<b>SG-07-09</b> <i>Bearing 037 - Dip 45 - Length 106.6m</i>							
From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu ppm	Pb ppm	Zn ppm
99.75	100.55	0.8	1.02	147.1	80	552	1189
100.55	101.35	0.8	0.62	78.9	290	1300	1685
101.35	102.25	0.9	0.06	2.2	164	835	2108
102.25	102.95	0.7	2.051	297.9	4492	10070	23900

<b>SG-07-08</b> <i>Bearing 35 - Dip 55 - Length 377.8</i>							
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Pb (%)	Zn (%)
missed ore shoot	N/A	N/A	N/A	N/A	N/A	N/A	N/A

<b>SG-07-07</b> <i>Bearing 36 - Dip 44 - Length 281.55</i>							
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Pb (%)	Zn (%)
San Gonzalo Vein	247.75	250.35	2.6	2.85	351	1.04	0.66

<b>SG-07-06</b> <i>Bearing 47 - Dip 58 - Length 387.2m</i>							
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Pb (%)	Zn (%)
Santiago Vein	24.8	28.3	3.5	0.4	226	NS	NS
Cross Vein	280.65	280.9	0.25	0.5	2120	7.82	NS
San Gonzalo	367.35	371.5	3.85	0.1	11	NS	NS

<b>SG-07-05</b> <i>Bearing 51 - Dip 69 - Length 137m</i>							
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Pb (%)	Zn (%)
Santiago Vein	28.7	31.8	3.1	0.49	201	NS	NS
Includes	31.1	31.8	0.7	1.54	272	NS	NS

<b>SG-07-04 Bearing 45 - Dip 49 - Length 312.7</b>							
	<b>From (Metres)</b>	<b>To (Metres)</b>	<b>Down Hole Lengths (metres)</b>	<b>Au (g/t)</b>	<b>Ag (g/t)</b>	<b>Pb (%)</b>	<b>Zn (%)</b>
Santiago Vein	18.55	25	6.45	0.21	364	NS	NS
(includes)	20.85	21.9	1.05	0.29	990	0.21	NS
" "	21.9	22.8	0.9	0.49	433	0.16	NS
Cross Vein	31	34.05	3.05	0.18	86	0.17	NS
San Gonzalo HW	248.15	249.25	1.1	0.43	58	0.25	0.26
FW	258.75	259	0.25	2.66	114	4.8	4.22

<b>SG-07-03 Bearing 66 - Dip 43 - Length 315m</b>							
	<b>From (Metres)</b>	<b>To (Metres)</b>	<b>Down Hole Lengths (metres)</b>	<b>Au (g/t)</b>	<b>Ag (g/t)</b>	<b>Pb (%)</b>	<b>Zn (%)</b>
San Gonzalo Vein	187.45	188.7	1.25	3.57	341	0.6	0.87

<b>SG-07-02 Bearing 30 - Dip 48 - Length 323.7m</b>							
	<b>From (Metres)</b>	<b>To (Metres)</b>	<b>Down Hole Lengths (metres)</b>	<b>Au (g/t)</b>	<b>Ag (g/t)</b>	<b>Pb (%)</b>	<b>Zn (%)</b>
San Gonzalo Vein Hanging Wall Zone	214.65	219.1	4.45	6.11	583.8	1.4	2.54
San Gonzalo Vein Foot Wall Zone	252.65	256	3.35	6.91	21.1	1.55	2.33

<b>SG-07-01 Bearing 42 - Dip 60 - Length 386.8m</b>							
	<b>From (Metres)</b>	<b>To (Metres)</b>	<b>Down Hole Lengths (metres)</b>	<b>Au (g/t)</b>	<b>Ag (g/t)</b>	<b>Pb (%)</b>	<b>Zn (%)</b>
Santiago Vein	147	149.7	2.7	1.19	227	>1%	>1%
San Gonzalo Vein Hanging Wall Zone	357.3	362.15	4.85	0.64	343.2	0.36%	0.63%
San Gonzalo Vein Foot Wall Zone	372.65	375.05	2.4	2.41	712.4	0.50%	0.13%



AVINO SILVER & GOLD MINES LTD. 2006-2008 Elena Tolosa Zone drill results

<b>ET-08-08</b> <i>Intersected the main Avino vein 192.95-203.5m (10.3m), gold &amp; silver values were low</i>								
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	192.95	194.45	1.5	1.456	4.6	318	57	508
	194.45	195.95	1.5	0.431	4.4	329	256	502
	195.95	197.1	1.15	0.325	13.5	1523	2446	3813
	197.1	198.6	1.5	0.1	2.5	133	355	1688
Main Avino Vein	198.6	199.7	1.1	0.048	4.4	101	36	1206
	199.7	200.8	1.1	0.046	5.7	69	72	896
	200.8	201.75	0.95	0.203	27.2	120	301	627
	201.75	203.25	1.5	0.03	6.5	431	43	1048

<b>ET-08-07</b> <i>Drilled 150m east of ET 08-04 it did not intersect the Avino vein</i>								
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)

<b>ET-08-06</b> <i>Intersected the Avino vein 237.6-288,7m (51.1m), Au &amp; Ag values were low, copper of interest</i>								
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	237.6	238.25	0.65	0.14	74.2	3526	7260	909
	238.25	239.75	1.5	0.065	22.4	2260	344	383
	239.75	241.25	1.5	0.02	8.7	883	43	528
	241.25	242.75	1.5	0.115	10.1	2249	374	1981
	242.75	244.25	1.5	0.045	8.7	2641	40	631
	244.25	245.75	1.5	0.105	14.4	3472	87	651
	245.75	247.25	1.5	0.072	17.1	4780	41	876
	247.25	248.75	1.5	0.053	20.5	6107	100	950
	248.75	250.25	1.5	0.1	11	4619	191	1044
	250.25	251.75	1.5	0.12	10.4	4869	282	784
	251.75	253.25	1.5	0.035	4	1261	45	662
	253.25	254.75	1.5	0.163	14.9	2553	78	835
	254.75	256.25	1.5	0.045	25.4	6483	95	734
	256.25	257.75	1.5	0.015	12	5544	40	871
	257.75	259.25	1.5	0.025	39.8	5758	217	521
	259.25	260.75	1.5	0.025	20.6	6136	89	465
Main Avino Vein	260.75	262.25	1.5	0.015	10.5	3202	74	327
	262.25	263.75	1.5	0.059	24	3670	105	533
	263.75	265.25	1.5	0.049	28.7	3252	183	718
	265.25	266.75	1.5	0.053	14.2	6129	112	584
	266.75	268.25	1.5	0.156	47.3	7192	217	399
	268.25	269.75	1.5	0.102	19.8	3342	125	326
	269.75	271.25	1.5	0.03	9.1	4101	38	414
	271.25	272.75	1.5	0.01	9.3	2611	94	455
	272.75	274.25	1.5	0.02	7.9	3355	41	391
	274.25	275.75	1.5	0.02	16.5	4405	58	496
	275.75	277.25	1.5	0.076	82.7	4570	422	979
	277.25	278.75	1.5	0.084	58.4	5545	956	593
	278.75	280.25	1.5	0.01	16.6	5749	74	659
	280.25	281.75	1.5	0.02	18.7	4592	68	575
	281.75	283.25	1.5	0.015	16.1	4219	74	651
	283.25	284.75	1.5	0.038	23.6	3526	7260	909
Main Avino Vein	284.75	286.25	1.5	<0.005	6.7	2841	22	1225
	286.25	287.75	1.5	0.092	49.4	25700	44	2712
	287.75	288.7	0.95	0.105	62.5	27200	57	2669

<b>ET-08-05</b> <i>Intersected the Avino vein 293.35-302.7 (9.35m) low Au &amp; Ag, copper values are of interest</i>								
	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	290.95	292.3	1.35	0.172	16.7	533	3964	643
	292.3	293.35	1.05	0.096	0.5	581	5078	2842
	293.35	294.85	1.5	0.379	30.8	2116	8000	559
	294.85	296.35	1.5	0.05	12.3	2654	7063	582
Main Avino Vein	296.35	297.6	1.25	0.568	67.3	3564	3688	164
	297.6	299.1	1.5	0.062	42.4	5360	1771	688
	299.1	300.6	1.5	0.02	31.8	14900	896	3473
	300.6	301.7	1.1	0.06	34.4	11300	282	1743
	301.7	302.7	1	0.13	44.2	10000	469	1265

ET-08-04

## Intersected the Avino Vein from 321-341.1m (20.1m) 128 g/t Ag, 0.04 g/t Au

	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	307.5	308.6	1.1	0.02	6.6	594	434	1291
	308.6	309.9	1.3	0.034	0.3	43	203	272
	311.9	312.6	0.7	0.115	27.2	2661	635	1330
	315	316.5	1.5	0.063	9.3	1558	257	1115
	316.5	318	1.5	0.065	19.1	4899	367	1122
	318	319.5	1.5	0.04	13	900	441	1265
	319.5	321	1.5	0.071	12.7	1765	400	846
	321	322.5	1.5	0.501	34.2	2378	264	426
	322	324	2	1.146	71	3147	421	496
	324	325.5	1.5	0.904	55.2	4652	230	288
	325.5	327	1.5	0.262	54.9	1395	203	236
	327	328.5	1.5	2.174	165	8408	509	286
	328.5	330	1.5	0.173	101.9	7194	8582	3727
	330	331.5	1.5	0.053	56	4926	5923	18300
	331.5	333	1.5	0.095	54.9	4081	2559	561
	333	334	1	0.08	23.1	1089	1199	301
	334	336	2	0.052	56.6	11000	536	597
	336	337.5	1.5	0.03	49.7	10900	170	618
	337	339	2	0.032	156.6	14700	395	853
	339	340	1	0.025	48.4	6149	174	595
	340	341.1	1.1	0.064	161.8	8252	2170	1765
	341	342.6	1.6	0.042	38.4	2734	662	1564
	342.63	344.1	1.47	0.025	34	8428	193	1194
	344.1	345.6	1.5	0.082	14.4	7693	109	826
	345.6	347.1	1.5	0.086	13.4	3645	113	435
	347.1	348.6	1.5	0.025	6.5	2553	51	203
	348.6	350.1	1.5	<0.005	3.2	2505	9	379
	350	351.6	1.6	0.058	68.5	254	415	369
	351.6	352.7	1.1	0.01	5.4	657	25	276

ET-08-03

	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	79.75	80.4	0.65	0.02	14.7	409	40	2080
	80.4	81.9	1.5	1.396	48	2641	148	435
	81.9	83.2	1.3	6.72	174.4	2456	327	21
	83.2	84.5	1.3	3.703	96.4	1815	818	94
	84.5	85.7	1.2	0.11	8.9	315	241	217
	192.25	193.75	1.5	0.275	24.6	257	618	318
	193.75	195.2	1.45	0.458	20.4	1528	298	330
	195.2	196.7	1.5	0.185	11.5	405	253	275
	196.7	198.3	1.6	0.294	40.4	760	449	147
	198.3	199.65	1.35	0.145	29.7	520	687	391
	199.65	200.95	1.3	0.065	20.1	1592	5318	570
	200.95	202.45	1.5	0.087	0.3	631	331	750
	202.45	203.95	1.5	0.082	3.8	432	167	487
	212.8	213.8	1	0.162	4.9	517	1910	584
	213.8	214.55	0.75	0.02	4.5	484	4282	3006
	214.55	216.05	1.5	0.135	21.2	490	301	1090
	216.05	217.55	1.5	0.109	40.8	393	893	489
	217.55	219.05	1.5	3.017	113.2	1830	1120	636
	219.05	220.55	1.5	0.096	7.9	1170	229	989
	220.55	222.05	1.5	0.025	8.8	967	307	668
	222.05	223.55	1.5	0.128	11.9	1546	117	585
	223.55	225.05	1.5	0.049	9.6	1875	229	671
	225.05	226.05	1	0.105	8.4	1269	122	641
	226.55	228.05	1.5	0.084	21.1	499	1455	1210
	228.05	229.55	1.5	0.1	21.7	272	441	784
	229.55	231.05	1.5	0.723	82.3	2988	596	599
	231.05	232.55	1.5	1.31	94.9	3753	565	674
	232.55	234.05	1.5	1.89	58.4	574	474	619
	234.05	235.55	1.5	1.658	69.1	1117	412	687
	235.55	237.05	1.5	2.756	53	2590	396	711
	237.05	238.55	1.5	1.065	28.7	1816	280	410
	238.55	240.05	1.5	0.219	66.5	1263	916	416
	240.05	241.55	1.5	0.185	45.3	369	191	424
	241.55	243.05	1.5	0.167	42	1220	482	438
	243.05	244.55	1.5	0.382	48.1	8097	525	2111
	244.55	246.05	1.5	0.648	60.7	1638	766	716
	246.05	247.55	1.5	0.506	49.7	1311	549	415
	247.55	249.05	1.5	0.125	39.7	1343	911	475
	249.05	250.55	1.5	0.16	78.1	3430	790	737
	250.55	252.05	1.5	0.135	92.9	3617	551	506
	252.05	253.55	1.5	0.13	44.4	5739	351	603
	253.55	255.05	1.5	0.07	42.6	3395	796	357
	255.05	256.55	1.5	0.045	30	2971	365	374
	256.55	257.85	1.3	0.025	31.4	5772	1510	686
	257.85	259.35	1.5	<0.005	<0.1	133	374	1041
	259.35	260.85	1.5	<0.005	2.6	469	114	935
	260.85	262.35	1.5	<0.005	1.1	457	94	1548

## ET-08-02

	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	68.4	70.2	1.8	<0.005	91.6	1008	196	324
	70.2	71	0.8	0.342	1.3	326	149	3386
	71	72.2	1.2	0.065	11.1	1480	53	922
	72.2	73.3	1.1	0.981	130	1150	472	192
	73.3	74.4	1.1	0.931	72.9	321	237	69
	74.4	75.1	0.7	0.026	4.8	1082	127	924
	164.55	166.15	1.6	0.065	33.4	3343	2393	688
	166.15	166.85	0.7	0.115	16.5	2433	740	329
	166.85	167.5	0.65	0.614	35.8	354	301	176
	170.05	170.4	0.35	0.276	39.4	2779	359	462
	178.55	179.5	0.95	0.281	24.9	383	102	1900
	185.55	186.75	1.2	0.236	2.4	82	41	2177
	186.75	188.25	1.5	0.215	6.4	138	50	1358
	188.25	189.75	1.5	0.585	8.6	766	561	1079
	189.75	191.25	1.5	2.635	19.4	692	724	817
	191.25	192.75	1.5	3.225	12	113	95	612
	192.75	194.25	1.5	2.08	27.7	224	125	595
	194.25	195.75	1.5	<0.005	40.5	1734	454	847
	195.75	197.25	1.5	<0.005	3.4	28	184	1074
	197.25	198.75	1.5	<0.005	4	42	168	690
	198.75	200.25	1.5	<0.005	4.9	201	352	1042
	200.25	201.75	1.5	<0.005	10.6	276	162	670
	201.75	203.25	1.5	<0.005	20.3	68	320	1091
	203.25	204.75	1.5	0.035	12.7	226	413	871
	204.75	206.25	1.5	<0.005	32.2	751	317	530
	206.25	207.75	1.5	<0.005	8.5	1200	83	410
	207.75	209.25	1.5	<0.005	10.3	957	134	660
	209.25	210.75	1.5	<0.005	25.5	1180	185	522
	210.75	212.25	1.5	<0.005	22.9	2220	423	3806
	212.25	213.5	1.25	<0.005	36.9	400	473	2021
	213.5	215	1.5	<0.005	3.1	217	85	1775
	215	216.5	1.5	<0.005	21.1	2919	365	2243
	216.5	218	1.5	<0.005	0.4	118	33	3004
	218	219.5	1.5	<0.005	1.1	66	34	2246
	219.5	221	1.5	0.136	8.1	145	126	905

## ET-08-01

	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	84.35	85.05	0.7	0.045	43.3	8621	168	240
	192.95	194.4	1.45	0.02	2.6	64	49	1029
	194.4	195.4	1	0.084	6	738	670	1076
	195.4	196.9	1.5	0.125	5	263	267	2706
	196.9	198.4	1.5	0.322	3.6	259	149	719
	198.4	199.9	1.5	0.02	7.8	97	68	554
	199.9	201.4	1.5	0.054	5.2	331	180	665
	201.4	202.9	1.5	<0.005	2.4	306	45	2079
	202.9	204.4	1.5	0.09	1.6	271	54	5950
	204.4	205.9	1.5	0.005	0.6	456	25	2784
	205.9	207.4	1.5	<0.005	0.8	168	16	4381
	207.4	208.9	1.5	<0.005	0.8	229	18	2361
	208.9	210.4	1.5	0.04	1.3	178	34	3494
	210.4	211.9	1.5	0.015	0.3	320	23	2502
	211.9	213.4	1.5	0.005	3	621	29	3857
	213.4	214.3	0.9	0.005	1.6	1134	479	3560
	214.3	216.25	1.95	0.015	10.4	1452	1308	3269
	216.25	217.75	1.5	<0.005	4.1	1732	2163	2690
	217.75	219.25	1.5	<0.005	12.2	1563	2077	1292
	219.25	220.75	1.5	0.044	9.4	913	1562	1029
	220.75	221.49	0.74	<0.005	19.9	1993	1896	4123



AVINO SILVER &  
GOLD MINES LTD.  
2006-07 Elena Tolosa Zone Assays

<b>ET-07-010</b> <i>Bearing 336 Dip -63 Length 308.7m</i>						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu g/t
Avino quartz vein with sulphides	257.3	258.8	1.5	0.16	85.3	15700
Avino quartz vein with sulphides	258.8	260.3	1.5	0.08	86.6	23400
Avino quartz vein with sulphides	260.3	261.8	1.5	0.125	27.7	14100
Avino quartz vein with sulphides	261.8	263.3	1.5	0.101	21.8	15400
Avino quartz vein with sulphides	263.3	264.8	1.5	0.098	20.3	13500
Avino quartz vein with sulphides	266.3	267.8	1.5	0.574	43.4	6613
Avino quartz vein with sulphides	267.8	269.3	1.5	0.457	39.8	4211
Avino quartz vein with sulphides	269.3	270.8	1.5	0.089	19.3	15200
Avino quartz vein with sulphides	282.8	284.3	1.5	0.02	9.3	16000
Avino quartz vein with sulphides	284.3	285.8	1.5	0.01	10.2	19300
Avino quartz vein with sulphides	285.8	287.3	1.5	0.035	27	31600
Avino quartz vein with sulphides	287.3	288.8	1.5	0.07	37.4	21500
Avino quartz vein with sulphides	288.8	290.3	1.5	0.049	27.1	34200
Avino quartz vein with sulphides	290.3	291.8	1.5	0.065	51.3	72600
Avino quartz vein with sulphides	291.8	293.3	1.5	0.02	14.8	33300
Avino quartz vein with sulphides	293.3	294.8	1.5	0.335	28.8	15000
Avino quartz vein with sulphides	294.8	295.8	1	0.035	23.2	17200
Avino quartz vein with sulphides	295.8	297.3	1.5	1.31	37.9	16100
Avino quartz vein with sulphides	297.3	299.1	1.8	0.51	51.5	7570

<b>ET-07-09</b> <i>Bearing 336 Dip -62 Length 328.6m</i>						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu g/t
Avino vein with massive chalopyrite	290.8	292.3	1.5	0.04	101.9	12100
Avino vein with massive chalopyrite	292.3	293.8	1.5	0.16	0.69	11500
Avino vein with massive chalopyrite	295.3	296.8	1.5	0.146	0.94	11200
Avino vein with massive chalopyrite	299.8	301.3	1.5	0.07	1.49	6327
Avino vein with massive chalopyrite	301.3	302.8	1.5	0.36	1.18	14600
Avino vein with massive chalopyrite	302.8	304.3	1.5	0.015	0.53	8029
Avino vein with massive chalopyrite	304.3	305.8	1.5	0.02	0.82	8475

<b>ET-07-08</b> <i>Bearing 346.65 Dip -69 Length 339.7m</i>						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu g/t
Avino vein. Moderate diss cpy-py	355.85	357.35	1.5	0.111	257.5	6959
Avino vein. Moderate diss cpy-py	357.35	359.15	1.8	0.125	170	9341

<b>ET-07-07</b> <i>Bearing 330 Dip -59 Length 304.85m</i>						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu g/t
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	272.3	273.8	1.5	0.615	80.6	2199
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	273.8	275.3	1.5	0.148	160.9	20500
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	275.3	276.8	1.5	0.118	203.5	19700
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	276.8	278.3	1.5	0.28	172.8	17800
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	278.3	279.8	1.5	0.368	441.4	24600
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	279.8	281.3	1.5	0.22	327	12600
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	281.3	282.8	1.5	0.081	110.8	3002
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	282.8	284.3	1.5	0.065	184.6	3317
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	284.3	285.8	1.5	0.07	89.2	8786
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	285.8	287.3	1.5	0.07	209.3	54400
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	287.3	288.8	1.5	0.035	32.8	13200
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	288.8	290.3	1.5	0.047	76.1	29300
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	290.3	291.8	1.5	0.126	339.7	44300
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	291.8	293.3	1.5	0.06	20.8	6361
Avino Vein. Wh Qtz veining w/moderate diss cpy and str	293.3	295.15	1.85	0.202	166.9	55500

<b>ET-07-06 Bearing 336 Dip -55 Length 320.05m</b>						
<b>Description</b>	<b>From (Metres)</b>	<b>To (Metres)</b>	<b>Down Hole Lengths (metres)</b>	<b>Au (g/t)</b>	<b>Ag (g/t)</b>	<b>Cu g/t</b>
Avino vein Wh qtz stockwork veining textures w'diss py-	289	290.5	1.5	0.95	228.9	23200
Avino vein Wh qtz stockwork veining textures w'diss py-	298	299.5	1.5	0.165	72.3	14800
Avino vein Wh qtz stockwork veining textures w'diss py-	299.5	301	1.5	0.485	54.6	8401
Avino vein Wh qtz stockwork veining textures w'diss py-	301	302.5	1.5	0.09	40.8	11500
Avino vein Wh qtz stockwork veining textures w'diss py-	302.5	304	1.5	0.147	55.6	14400
Avino vein Wh qtz stockwork veining textures w'diss py-	304	305.5	1.5	0.093	55.8	8321
Avino vein Wh qtz stockwork veining textures w'diss py-	305.5	307	1.5	1.59	90.4	15100
Avino vein Wh qtz stockwork veining textures w'diss py-	307	308.6	1.5	0.15	73.8	8729
Intrusive rock. Wh qtz veining w/cpy	308.6	310.1	1.5	0.04	54.6	5962
Intrusive rock. Wh qtz veining w/cpy	310.1	311.6	1.5	0.075	98	6217
Intrusive rock. Wh qtz veining w/cpy	311.6	313.1	1.5	0.075	81.9	10800
Intrusive rock. Wh qtz veining w/cpy	313.1	314.6	1.5	0.04	97.9	7765

<b>ET-07-05 Bearing 333 Dip -66 Length 351.5m</b>						
<b>Description</b>	<b>From (Metres)</b>	<b>To (Metres)</b>	<b>Down Hole Lengths (metres)</b>	<b>Au (g/t)</b>	<b>Ag (g/t)</b>	<b>Cu g/t</b>
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	301.95	303.45	1.5	1.152	83	1971
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	303.45	304.95	1.5	1.483	26.7	683
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	304.95	306.45	1.5	2.119	36.9	2030
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	312.45	312.95	0.5	1.752	10.7	533
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	312.95	315.45	2.5	1.015	119.7	1268
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	315.45	316.95	1.5	0.195	204.2	8565
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	316.95	318.45	1.5	0.075	123.6	2212
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	319.95	321.45	1.5	0.155	86.2	20300
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	321.45	322.95	1.5	0.12	30.4	13000
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	322.95	324.45	1.5	0.115	45.2	15400
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	324.45	325.95	1.5	0.075	40.2	18400
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	325.95	327.45	1.5	0.07	27.5	10200
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	327.45	328.95	1.5	0.05	48.1	17500
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	328.95	330.45	1.5	0.053	38.2	16700
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	330.45	331.95	1.5	0.095	61.9	20200
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	331.95	333.45	1.5	0.144	75.2	18900
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	333.45	334.95	1.5	0.13	45.7	15800
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	337.95	339.45	1.5	0.328	69	12200
Avino vein. Wh qtz stkwk-veining w/diss f.g cpy+py+sped	339.45	340.95	1.5	0.236	41	12200

<b>ET-07-04 Bearing 331 Dip -56 Length 318.7m</b>						
<b>Description</b>	<b>From (Metres)</b>	<b>To (Metres)</b>	<b>Down Hole Lengths (metres)</b>	<b>Au (g/t)</b>	<b>Ag (g/t)</b>	<b>Cu g/t</b>
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	271.45	272.95	1.5	0.155	44.1	3618
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	272.95	274.45	1.5	0.397	106.1	2842
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	274.45	275.95	1.5	1.08	76.1	3862
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	275.95	277.45	1.5	1.314	126.9	4010
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	277.45	278.95	1.5	0.874	53	381
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	278.95	280.45	1.5	0.534	61.4	675
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	280.45	281.95	1.5	0.436	97.3	2649
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	287.95	289.45	1.5	0.25	63.5	7555
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	289.45	290.95	1.5	0.101	31.4	5156
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	290.95	292.45	1.5	1.115	138.6	3558
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	292.45	293.95	1.5	0.151	86.3	4162
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	293.95	295.45	1.5	0.161	34.9	3521
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	295.45	296.95	1.5	0.568	41.6	5047
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	296.95	298.45	1.5	0.115	29.1	10000
Avino Vein. Wh qtz veining w/ fine grain diss cpy-py	298.45	300.1	1.65	0.08	29.8	8408

<b>ET-07-03</b> <i>Bearing 336 Dip -71 Length 349.5</i>						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu g/t
Avino vein. Oxidized material	280.75	282.25	1.5	7.68	121.9	6048
Avino vein. Oxidized material	282.25	283.75	1.5	6.034	196.3	5034
Avino vein. Oxidized material	283.75	285.25	1.5	1.692	69.9	10400
Avino vein. Oxidized material	285.25	286.75	1.5	13.988	295.3	19600
Avino vein. Oxidized material	286.75	288.25	1.5	4.731	104.7	16100
Avino vein. Oxidized material	288.25	289.75	1.5	2.158	103.7	3948
Avino vein. Oxidized material	289.75	291.25	1.5	0.158	31.5	3789
Avino vein. Oxidized material	291.25	292.75	1.5	2.411	60	2683
Avino vein. Oxidized material	292.75	294.25	1.5	2.733	27.5	2793
Avino vein. Oxidized material	294.25	295.75	1.5	0.548	89.6	7268
Avino vein. Silicified quartz with diss cpy-py-specularite	295.75	297.25	1.5	3.086	161.8	5934
Avino vein. Silicified quartz with diss cpy-py-specularite	297.25	298.75	1.5	7.954	75.7	1476
Avino vein. Silicified quartz with diss cpy-py-specularite	298.75	300.25	1.5	2.265	97	10500
Avino vein. Silicified quartz with diss cpy-py-specularite	300.25	301.75	1.5	1.057	60.4	1486
Avino vein. Silicified quartz with diss cpy-py-specularite	301.75	303.25	1.5	1.911	42	3258

<b>ET-07-02</b> <i>Bearing 358 - Dip 75 - Length 311.9m</i>						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)
no significant assays						

<b>ET-07-01</b> <i>Bearing 1 Dip -69 Length 298.6m</i>						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)
Avino Vein. Silicified quart with diss cpy-py-specularite	284.9	285.85	0.95	0.068	201.7	3149
Avino Vein. Silicified quart with diss cpy-py-specularite	285.85	286.8	0.95	0.025	35.4	969
Avino Vein. Silicified quart with diss cpy-py-specularite	286.8	287	0.2	0.226	808.8	100200
Avino Vein. Silicified quart with diss cpy-py-specularite	287	288.5	1.5	0.045	27.3	2540
Avino Vein. Silicified quart with diss cpy-py-specularite	288	290	1.5	0.052	101.6	10000

<b>ET-06-04</b> <i>Bearing 340 Dip -50 Length 444.05m</i>						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)
Avino Vein	272.4	273.4	1.00	0.35	8.0	900
Avino Vein	273.4	274.4	1.00	0.004	0.5	30
Avino Vein	274.4	275.4	1.00	0.004	6.4	780
Avino Vein	275.4	276.4	1.00	0.004	1.4	63
Avino Vein	276.4	277.4	1.00	0.004	4.5	430
Avino Vein	277.4	278.4	1.00	0.004	1.0	51
Avino Vein	278.4	279.4	1.00	0.05	5.1	235
Avino Vein	279.4	280.4	1.00	0.004	1.3	77
Avino Vein	280.4	281.4	1.00	0.04	4.2	223
Avino Vein	281.4	282.4	1.00	0.015	2.6	185
Avino Vein	282.4	283.4	1.00	0.059	12.0	1710
Avino Vein	283.4	284.4	1.00	0.01	1.2	111
Avino Vein	284.4	285.4	1.00	0.196	28.1	5900
Avino Vein	285.4	286.4	1.00	0.035	4.7	530
Avino Vein	286.4	287.4	1.00	0.004	2.6	520
Avino Vein	287.4	287.4	0.00	0.015	2.4	214
Avino Vein	288.4	289.4	1.00	0.02	2.6	840
Avino Vein	289.4	290.4	1.00	0.004	1.5	185
Avino Vein	290.4	291.4	1.00	0.075	33.3	7500
Avino Vein	291.4	292.4	1.00	0.03	6.0	1250
Avino Vein	292.4	293.4	1.00	0.15	10.9	910
Avino Vein	293.4	294.4	1.00	0.08	66.0	11500
Avino Vein	294.4	295.4	1.00	0.15	21.0	1380
Avino Vein	295.4	296.4	1.00	0.004	1.5	211
Avino Vein	296.4	297.4	1.00	0.04	7.2	810
Avino Vein	297.4	298.4	1.00	0.05	13.3	1690
Avino Vein	298.4	299.4	1.00	0.01	2.8	149
Avino Vein	299.4	300.4	1.00	0.045	4.0	319
Avino Vein	300.4	301.4	1.00	0.015	5.0	375
Avino Vein	301.4	302.4	1.00	0.06	9.2	630

Avino Vein	302.4	303.4	1.00	0.095	28.6	6400
Avino Vein	303.4	304.4	1.00	0.07	10.2	1130
Avino Vein	304.4	305.4	1.00	0.045	9.3	430
Avino Vein	305.4	306.4	1.00	0.085	12.0	550
Avino Vein	306.4	307.4	1.00	0.155	28.0	2050
Avino Vein	307.4	308.45	1.05	0.37	31.0	1480
Avino Vein	308.45	309.45	1.00	0.04	24.3	1000
Avino Vein	309.45	310.45	1.00	0.065	17.6	1120
Avino Vein	310.45	311.45	1.00	0.185	7.0	308
Avino Vein	311.45	312.45	1.00	0.12	7.1	720
Avino Vein	312.45	313.45	1.00	0.08	3.1	107
Avino Vein	313.45	314.45	1.00	0.418	100.0	1760
Avino Vein	314.45	315.45	1.00	0.07	7.0	153
Avino Vein	315.45	316.45	1.00	0.28	29.0	1480
Avino Vein	316.45	317.45	1.00	0.22	13.2	1450
Avino Vein	317.45	318.45	1.00	0.06	36.0	1500
Avino Vein	318.45	319.45	1.00	0.25	545.8	7500
Avino Vein	319.45	320.45	1.00	0.05	96.0	5900
Avino Vein	320.45	321.45	1.00	0.105	72.0	8500
Avino Vein	321.45	322.45	1.00	0.035	23.0	8700
Avino Vein	322.45	323.45	1.00	0.054	25.4	7500
Avino Vein	323.45	324.45	1.00	0.03	41.6	10400
Avino Vein	324.45	325.45	1.00	0.04	43.6	14700
Avino Vein	325.45	326.45	1.00	0.075	41.5	9900
Avino Vein	326.45	327.45	1.00	0.065	45.0	8800
Avino Vein	327.45	328.45	1.00	0.06	55.0	3880
Avino Vein	328.45	329.45	1.00	0.144	42.0	6800
Avino Vein	329.45	330.45	1.00	0.17	40.0	7300
Avino Vein	330.45	331.45	1.00	1.24	80.0	22000
Avino Vein	331.45	332.45	1.00	0.653	157.0	22000
Avino Vein	332.45	333.45	1.00	1.051	176.0	21400
Avino Vein	333.45	334.45	1.00	0.12	111.0	13000
Avino Vein	334.45	335.45	1.00	0.12	78.0	18300
Avino Vein	335.45	336.45	1.00	0.125	80.0	16500
Avino Vein	336.45	337.45	1.00	0.205	33.6	7500
Avino Vein	337.45	338.45	1.00	0.3	53.0	4050
Avino Vein	338.45	339.45	1.00	0.04	38.4	11500
Avino Vein	339.45	340.45	1.00	0.015	2.6	950
Avino Vein	340.45	341.45	1.00	0.015	15.5	2450
Avino Vein	341.45	342.6	1.15	0.015	20.5	8900
Avino Vein	342.6	343.75	1.15	0.01	7.0	960
Avino Vein	343.75	344.75	1.00	0.02	17.4	4010
Avino Vein	344.75	345.75	1.00	0.004	4.0	1650
Avino Vein	345.75	346.75	1.00	0.004	4.2	169

<b>ET-06-03</b>						
<i>Bearing 339 Dip -48 Length 421.15m</i>						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)
HW SPLIT	327.40	328.40	1.00	0.015	2.9	325
HW SPLIT	328.40	329.40	1.00	0.17	17.1	1161
HW SPLIT	329.40	330.45	1.05	0.055	0.4	239
HW SPLIT	330.45	331.45	1.00	0.59	1.1	244
HW SPLIT	331.45	332.45	1.00	0.004	0	40
HW SPLIT	332.45	333.50	1.05	0.281	1.6	70
HW SPLIT	333.50	334.50	1.00	0.015	0	56
HW SPLIT	334.50	335.50	1.00	0.004	0	41
HW SPLIT	335.50	336.60	1.10	0.01	1.9	213
HW SPLIT	336.60	337.60	1.00	0.385	0.8	326
HW SPLIT	337.60	338.60	1.00	0.345	0.4	187
HW SPLIT	338.60	339.60	1.00	1.29	6.5	1077
HW SPLIT	339.60	340.60	1.00	0.185	11.3	8208
HW SPLIT	340.60	341.60	1.00	0.12	0	127
HW SPLIT	341.60	342.60	1.00	0.035	0	54
HW SPLIT	342.60	343.60	1.00	0.27	3.1	227
HW SPLIT	343.60	344.65	1.05	0.38	2.5	686
HW SPLIT	344.65	345.65	1.00	0.191	1.6	406

HW SPLIT	345.65	346.65	1.00	0.533	1.7	319
HW SPLIT	346.65	347.70	1.05	0.04	0.5	283
HW SPLIT	347.70	348.70	1.00	0.369	16.5	1799
HW SPLIT	348.70	349.70	1.00	0.24	6.6	932
HW SPLIT	349.70	350.75	1.05	0.579	7.5	330
HW SPLIT	350.75	351.75	1.00	0.584	63.4	5402
HW SPLIT	351.75	352.75	1.00	1.725	32.8	2596
HW SPLIT	352.75	353.80	1.05	1.211	27.4	3353
HW SPLIT	353.80	355.05	1.25	1.923	25	1614
AVINO VEIN	368.25	369.25	1.00	0.449	68.3	3580
AVINO VEIN	369.25	370.30	1.05	0.595	224.7	1474
AVINO VEIN	370.30	371.30	1.00	0.303	68.5	2016
AVINO VEIN	371.30	372.30	1.00	0.105	62.5	1390
AVINO VEIN	372.30	373.35	1.05	0.212	132.5	3088
AVINO VEIN	373.35	374.35	1.00	0.185	238.7	9637
AVINO VEIN	374.35	375.35	1.00	0.085	34.9	1796
AVINO VEIN	375.35	376.05	0.70	0.135	142.8	5590
AVINO VEIN	376.05	377.05	1.00	0.109	71	2789
AVINO VEIN	377.05	378.05	1.00	0.25	74	4069
AVINO VEIN	378.05	379.10	1.05	0.133	91.4	6007
AVINO VEIN	379.10	380.40	1.30	0.055	49.3	10000
AVINO VEIN	380.40	381.40	1.00	0.06	90.4	16300
AVINO VEIN	381.40	382.40	1.00	0.04	74.5	24900
AVINO VEIN	382.40	383.45	1.05	0.035	45.6	10900
AVINO VEIN	383.45	384.50	1.05	0.03	36.6	12200
AVINO VEIN	384.50	385.65	1.15	0.435	46.5	16300
AVINO VEIN	385.65	386.65	1.00	0.045	65.2	12100
AVINO VEIN	386.65	387.65	1.00	0.01	27	3893
AVINO VEIN	387.65	388.70	1.05	0.025	34.7	4745
AVINO VEIN	388.70	389.90	1.20	0.035	34.3	4675
AVINO VEIN	389.90	390.90	1.00	0.13	31.2	8051

<b>ET-06-02</b>						
<b>Bearing 340 Dip -50 Length 416.7m</b>						
<b>Description</b>	<b>From (Metres)</b>	<b>To (Metres)</b>	<b>Down Hole Lengths (metres)</b>	<b>Au (g/t)</b>	<b>Ag (g/t)</b>	<b>Cu (g/t)</b>
Avino Vein	324.95	326.00	1.05	0.035	5.5	309
Avino Vein	326.00	327.00	1.00	0.04	32	72
Avino Vein	327.00	328.00	1.00	0.004	2	62
Avino Vein	328.00	328.75	0.75	0.04	10	48
Avino Vein	328.75	329.75	1.00	0.045	6.2	768
Avino Vein	329.75	330.75	1.00	0.01	6.2	731
Avino Vein	330.75	331.80	1.05	0.144	6.8	917
Avino Vein	331.80	332.80	1.00	0.01	1.6	204
Avino Vein	332.80	333.80	1.00	0.03	5.3	930
Avino Vein	333.80	334.85	1.05	0.045	25	3411
Avino Vein	334.85	335.85	1.00	0.004	4.3	981
Avino Vein	335.85	336.85	1.00	0.01	4	1187
Avino Vein	336.85	337.90	1.05	0.02	20	259
Avino Vein	337.90	338.90	1.00	0.01	1	138
Avino Vein	338.90	339.90	1.00	0.004	1.5	380
Avino Vein	339.90	340.95	1.05	0.065	7.2	1985
Avino Vein	340.95	341.95	1.00	0.045	16	5461
Avino Vein	341.95	342.95	1.00	0.305	4.7	1371
Avino Vein	342.95	344.00	1.05	0.075	14.2	5834
Avino Vein	344.00	345.00	1.00	0.054	15	2054
Avino Vein	345.00	346.00	1.00	0.035	9	3386
Avino Vein	346.00	347.05	1.05	0.025	4.6	2267
Avino Vein	347.05	347.75	0.70	0.319	9	3007
Avino Vein	347.75	348.75	1.00	1.085	14	3692
Avino Vein	348.75	349.75	1.00	2.044	27.6	6363
Avino Vein	349.75	350.80	1.05	0.622	9.6	3094
Avino Vein	350.80	351.80	1.00	0.315	12	1554
Avino Vein	351.80	352.80	1.00	0.13	11	1785
Avino Vein	352.80	353.85	1.05	0.145	8.3	2966
Avino Vein	353.85	354.85	1.00	2.568	18	6847
Avino Vein	354.85	355.85	1.00	0.195	14	4514

Avino Vein	355.85	356.90	1.05	0.19	30	6402
Avino Vein	356.90	357.95	1.05	0.41	60	7928
Avino Vein	357.95	359.00	1.05	0.295	10.5	1883
Avino Vein	359.00	360.05	1.05	4.31	41.6	7101
Avino Vein	360.05	361.05	1.00	0.485	9	2649
Avino Vein	361.05	362.05	1.00	0.45	8	1994
Avino Vein	362.05	363.05	1.00	0.09	4.4	1223
Avino Vein	363.05	364.05	1.00	2.329	17.7	5679
Avino Vein	364.05	365.10	1.05	0.045	14.4	2474
Avino Vein	365.10	366.40	1.30	0.353	18.4	9891
Avino Vein	366.40	367.70	1.30	1.549	100	7541
Avino Vein	367.70	368.70	1.00	1.24	16.7	2920
Avino Vein	368.70	369.70	1.00	0.215	13	2897
Avino Vein	369.70	370.75	1.05	0.201	35.2	5427
Avino Vein	370.75	371.75	1.00	0.285	27.6	4973
Avino Vein	371.75	372.75	1.00	0.978	50	6924
Avino Vein	372.75	373.80	1.05	0.11	32	3580
Avino Vein	373.80	374.80	1.00	0.51	57	1908
Avino Vein	374.80	375.80	1.00	0.365	57	4479
Avino Vein	375.80	376.80	1.00	0.769	45	5086
Avino Vein	376.80	377.90	1.10	1.24	50	10100
Avino Vein	377.90	379.90	1.00	0.675	52	9239
Avino Vein	379.90	380.90	1.00	0.1	47	3619
Avino Vein	380.90	381.90	1.00	0.045	18	1653
Avino Vein	381.90	382.95	1.05	0.035	12.1	4089
Avino Vein	382.95	383.55	0.60	0.015	8.5	1752
Avino Vein	383.55	384.55	1.00	0.05	10.2	3829
Avino Vein	384.55	385.55	1.00	0.088	19	3662
Avino Vein	385.55	386.60	1.05	0.03	44	1794
Avino Vein	386.60	387.65	1.05	0.125	35.7	2262
Avino Vein	387.65	388.75	1.10	0.158	126	7586
Avino Vein	388.75	389.75	1.00	0.06	21	3231
Avino Vein	389.75	390.75	1.00	0.045	10.7	2086
Avino Vein	390.75	391.80	1.05	0.89	26.8	3966
Avino Vein	391.80	392.80	1.00	1.49	36	4180
Avino Vein	392.80	393.80	1.00	0.195	13.5	2903
Avino Vein	393.80	394.95	1.15	0.095	24.5	4045
Avino Vein	394.95	395.95	1.00	0.035	11.3	1317
Avino Vein	395.95	396.95	1.00	0.06	21.9	1707
Avino Vein	396.95	398.00	1.05	0.01	2.5	378
Avino Vein	398.00	399.30	1.30	0.05	20.1	2242
Avino Vein	399.30	400.30	1.00	0.07	31.3	1927
Avino Vein	400.30	401.30	1.00	0.045	15.8	514
Avino Vein	401.30	402.35	1.05	0.025	28.1	497
Avino Vein	402.35	403.35	1.00	0.025	8.3	515
Avino Vein	403.35	404.35	1.00	0.04	1.3	61
Avino Vein	404.35	405.50	1.15	0.051	27.2	2913
Avino Vein	405.50	406.40	0.90	0.1	48	1326
Avino Vein	406.40	407.40	1.00	0.05	37.4	1259

<b>ET-06-01</b>						
<i>Bearing 337 Dip 90 Length 219.15m</i>						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)
Avino Vein	366.90	367.90	1.00	0.010	0.5	64
Avino Vein	367.90	368.90	1.00	0.005	19.4	952
Avino Vein	368.90	369.95	1.05	0.010	1.8	379
Avino Vein	369.95	370.95	1.00	0.030	33.7	2955
Avino Vein	370.95	371.95	1.00	0.049	40.0	2359
Avino Vein	371.95	373.00	1.05	0.010	4.8	607
Avino Vein	373.00	374.00	1.00	0.020	36.9	1985
Avino Vein	374.00	375.00	1.00	<0.005	1.1	194
Avino Vein	375.00	376.05	1.05	<0.005	8.2	1071
Avino Vein	376.05	376.80	0.75	<0.005	<0.1	122
Avino Vein	376.80	377.80	1.00	<0.005	2.1	326
Avino Vein	377.80	378.80	1.00	0.015	6.1	1046
Avino Vein	378.80	379.85	1.05	0.030	41.6	97

Avino Vein	379.85	380.85	1.00	0.020	3.0	658
Avino Vein	380.85	381.85	1.00	0.033	16.2	1530
Avino Vein	381.85	382.90	1.05	0.020	1.3	147
Avino Vein	382.90	383.90	1.00	0.015	8.5	451
Avino Vein	383.90	384.90	1.00	0.048	29.5	1735
Avino Vein	384.90	385.95	1.05	0.020	11.1	976
Avino Vein	385.95	386.95	1.00	0.078	45.9	3533
Avino Vein	386.95	387.95	1.00	0.055	44.5	510
Avino Vein	387.95	389.00	1.05	0.015	5.8	702
Avino Vein	389.00	390.00	1.00	<0.005	11.6	1651
Avino Vein	390.00	391.00	1.00	0.030	24.1	6692
Avino Vein	391.00	392.05	1.05	0.015	21.2	6118
Avino Vein	392.05	393.05	1.00	0.015	52.1	13800
Avino Vein	393.05	394.05	1.00	0.010	48.4	3282
Avino Vein	394.05	395.10	1.05	0.055	15.8	1193
Avino Vein	395.10	396.10	1.00	0.020	27.2	5666
Avino Vein	396.10	397.10	1.00	0.015	25.2	3589
Avino Vein	397.10	398.15	1.05	0.030	54.7	5950
Avino Vein	398.15	399.15	1.00	0.010	21.9	2030
Avino Vein	399.15	400.25	1.10	0.015	12.9	1927
Avino Vein	400.25	401.25	1.00	0.015	17.2	1346
Avino Vein	401.25	402.25	1.00	0.120	15.0	4123
Avino Vein	402.25	403.30	1.05	0.020	2.6	1266
Avino Vein	403.30	404.30	1.00	0.015	10.1	3046
Avino Vein	404.30	405.30	1.00	0.030	19.7	3607
Avino Vein	405.30	406.35	1.05	0.030	4.4	2202
Avino Vein	406.35	407.55	1.20	0.132	12.2	4958
Avino Vein	407.55	408.80	1.25	0.112	16.6	3099
Avino Vein	408.80	409.80	1.00	0.085	17.6	2568
Avino Vein	409.80	410.80	1.00	0.262	136.6	6680
Avino Vein	410.80	411.85	1.05	0.004	81.4	3346
Avino Vein	411.85	412.85	1.00	0.020	14.4	1248
Avino Vein	412.85	413.85	1.00	0.040	9.8	917
Avino Vein	413.85	414.90	1.05	0.060	11.7	826
Avino Vein	414.90	415.90	1.00	0.004	16.5	2209
Avino Vein	415.90	416.90	1.00	<0.005	11.0	733
Avino Vein	416.90	417.95	1.05	<0.005	6.4	682



**La Blanca Zone**

*Drilled 2 holes in 2008 (LBL-08-01 & 02)*

Neither hole intersected significant mineralization

**San Jose Area**

*Drilled 6 holes in 2008 (SJ-08-01 through SJ-08-06)*

No significant intersections were reported, except for SJ-08-03 which intersected 0.4 meters @0.745 g/t gold and 98.5 g/t Silver in what may be the La Estela vein. Minor intersections were reported in SJ-08-06.

**Santa Ana Area**

*Drilled 4 holes in 2008 (STA-08-1 through STA-08-04)*

Minor intersections reported in STA-08-04, but nothing significant

**Aguila Mexicana Area**

*Drilled 7 holes in 2008 (AM-08-1 through AM-08-07)*

Significant intersections were found in holes AM-08-02 & AM-08-04

**AM-08-02**

*intersected 5.05m @ 0.49 g/t gold & 75.38 g/t silver*

	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	195.05	195.9	0.85	0.221	189.4	155	238	438
	195.9	196.8	0.9	0.1	19.1	139	155	384
	196.8	197.9	1.1	0.245	82.6	738	14400	34000
	197.8	199.1	1.2	0.905	42.1	467	13800	46500
	199.1	200.1	1	1.046	77.1	1552	3977	0

**AM-08-04**

*intersected 3.30m grading 0.34 g/t gold & 151 g/t silver*

	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (ppm)	Pb (ppm)	Zn (ppm)
	205.1	206.15	1.05	0.309	85.4	1092	4672	4835
	206.15	207.15	1	0.259	132.7	3278	6480	1116
	207.15	207.8	0.65	0.6	277.4	1017	1979	1020
	207.8	208.4	0.6	0.243	159.4	693	786	693



## 2006 - 07 Drilling on Zones:

Aguila Mexicana zone (AM)  
 Charumbo Zone (CH)  
 Gap Zone (GAP)  
 Geophysical Anomaly (GFA)  
 Guadalupe Vein (GPE)  
 La Estela vein (LE)  
 Los Angeles zone (LA)  
 Nuestra Seniora (NS)  
 San Jose zone (SJ)  
 San Luis zone (SL)  
 San Pedro & Paulo Zones (SP&P)  
 Santa Ana zone (STA)  
 Santiago vein (ST)

### Aguila Mexicana zone (AM)

AM-07-01 Bearing - Dip - Length								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Fault zone	87.20	87.90	0.70	0.020	3.1	19	19	224
Aguila Mexicana vein	87.90	89.00	1.10	0.015	3.6	24	22	132
Aguila Mexicana vein	89.00	90.10	1.10	0.015	4.2	13	15	119
Aguila Mexicana vein	90.10	91.20	1.10	0.010	2.6	12	62	292
Aguila Mexicana vein	91.20	92.35	1.15	0.020	2.7	13	32	155
Fault zone	92.35	93.80	1.45	0.015	1.6	6	16	153
Qtz veining along core axe	106.00	106.40	0.40	0.062	7.7	22	26	48
Qtz veinlet with sulfurs	115.15	115.55	0.40	0.035	5.8	20	17	42
Wh qtx veining	157.10	157.60	0.50	0.044	41.4	21	707	915
Silicified tuff	157.60	158.60	1.00	<0.005	2.5	6	231	278
Qtz veinlet with sulfurs	158.60	159.00	0.40	0.766	399.2	74	2667	4751

### Churumbo zone (CH)

CH-06-03 Bearing 340 - Dip -50 - Length 453.75m						
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu g/t
	169.8	170.8	1.00	0.01	4	199
	170.8	171.8	1.00	0.004	5.3	583
	171.8	172.8	1.00	0.004	2	476
	172.8	173.8	1.00	0.01	3	168
	173.8	174.8	1.00	0.004	5	1541
	174.8	175.8	1.00	0.004	1.2	228
	175.8	176.8	1.00	0.015	2	53
	176.8	177.8	1.00	0.01	3	183
	177.8	178.8	1.00	0.004	5	1869
	178.8	179.8	1.00	0.004	7.7	1506
	179.8	180.8	1.00	0.03	12	1256
	180.8	181.8	1.00	0.015	7	698
	181.8	182.8	1.00	0.054	14	506
AVINO VEIN	182.8	183.8	1.00	0.1	21	1409
AVINO VEIN	183.8	184.8	1.00	0.02	7.4	1946
AVINO VEIN	184.8	185.8	1.00	0.045	11.5	6742
AVINO VEIN	185.8	186.8	1.00	1.064	52	3131
AVINO VEIN	186.8	187.8	1.00	0.06	125	2332
AVINO VEIN	187.8	188.8	1.00	0.025	35.5	3904
AVINO VEIN	188.8	189.8	1.00	0.01	20	2836
AVINO VEIN	189.8	190.8	1.00	0.01	5	792
AVINO VEIN	190.8	191.8	1.00	0.02	22	895
AVINO VEIN	191.8	192.8	1.00	0.01	42	4822
AVINO VEIN	192.8	193.8	1.00	0.025	39	5029
AVINO VEIN	193.8	194.8	1.00	0.004	11	909
	194.8	195.8	1.00	0.035	7	809
	195.8	196.8	1.00	0.004	37.4	1975
	196.8	197.8	1.00	0.025	18	4268
	197.8	198.8	1.00	0.004	5.7	1054
	198.8	199.8	1.00	0.01	13	1513
	199.8	200.8	1.00	0.004	10	1115
	200.8	201.8	1.00	0.055	18	1084

	201.8	202.8	1.00	0.045	16.6	895
	202.8	203.8	1.00	0.025	25	1296
	203.8	204.8	1.00	0.04	16.5	1788
FOOTWALL BRECCIA	204.8	205.8	1.00	0.02	56	2471
FOOTWALL BRECCIA	205.8	206.8	1.00	0.059	187	5297
FOOTWALL BRECCIA	206.8	207.8	1.00	0.015	18.7	1181
FOOTWALL BRECCIA	207.8	208.8	1.00	0.01	27	3081
FOOTWALL BRECCIA	208.8	209.8	1.00	0.02	11.2	3451
FOOTWALL BRECCIA	209.8	210.8	1.00	0.004	22	4732
FOOTWALL BRECCIA	210.8	211.8	1.00	0.01	103	4329
FOOTWALL BRECCIA	211.8	212.8	1.00	0.01	21	2569
FOOTWALL BRECCIA	212.8	213.8	1.00	0.015	16	1620
FOOTWALL BRECCIA	213.8	214.8	1.00	0.095	25	5673
FOOTWALL BRECCIA	214.8	215.8	1.00	3.973	77	873
FOOTWALL BRECCIA	215.8	216.8	1.00	0.325	65	1410
	216.8	217.8	1.00	0.055	4	67
	217.8	218.8	1.00	0.004	2	37
	218.8	219.8	1.00	0.004	2	30
	219.8	220.8	1.00	0.004	5	32

## Gap Zone (GAP)

<b>GAP-07-03</b> <i>Bearing 022 Dip -45 Length 212.9.75 m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Qtz veinlets with diss fine sulfid	69.50	69.70	0.20	0.121	102.5	55	4623	2823
Wh qtz veining w/moderate-st	137.85	138.35	0.50	<0.005	14.8	17	394	35700
Wh qtz veining w/moderate-st	138.35	139.15	0.80	0.005	7.7	146	1217	14500
Wh qtz veining w/moderate-st	139.15	140.80	1.65	0.065	9.4	349	1351	4732
Wh qtz veining w/moderate-st	140.80	141.65	0.85	0.052	6.0	218	815	1469
Wh qtz veining w/moderate-st	141.65	142.65	1.00	0.040	4.2	119	381	2314
Wh qtz veining w/moderate-st	142.65	143.45	0.80	0.109	5.7	147	294	2383
Wh qtz veining w/moderate-st	143.45	144.10	0.65	0.020	1.1	26	86	912
<b>GAP-07-02</b> <i>Bearing 010 Dip -45 Length 212.9 m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Wh qtz veinlet w/py and diss P	45.80	46.20	0.40	0.036	8.5	23	3445	1775
Gray qtz veinlet w/strong py	65.45	65.85	0.40	0.245	25.6	168	239	4468
Strong pyrite	70.20	71.20	1.00	0.075	3.1	37	270	668
vetilla con pirita y galena	97.20	97.50	0.30	0.040	33.7	57	20000	7910
vetilla con pirita y galena	120.25	120.75	0.50	0.210	100.1	1194	57500	2155
zona con abundante pirita	123.00	123.90	0.90	0.105	4.9	53	988	2221
zona de vetilleo con abundante	142.05	143.05	1.00	0.020	3.6	28	639	3052
veta con oxidacion	143.05	144.05	1.00	0.035	7.5	72	446	18500
zona de vetilleo con abundante	151.75	152.35	0.60	0.105	8.7	126	2768	1101
zona con abundante pirita y ga	221.75	222.35	0.60	0.020	1.5	18	2124	133
zona con abundante pirita con	252.35	253.25	0.90	<0.005	107.3	4334	2798	247
zona con abundante pirita con	256.25	257.15	0.90	0.025	62.0	3497	1053	693
zona con abundante pirita con	257.15	258.30	1.15	<0.005	1.4	219	82	98
zona con abundante pirita con	258.30	259.15	0.85	<0.005	3.5	1161	57	69

## Geophysical Anomaly (GFA)

<b>GFA-07-01</b> <i>Bearing 180 - Dip -60 - Length 360.75 m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
zona con abundante pirita	260.30	261.20	0.90	0.055	10.6	33	421	1908
zona con abundante pirita	261.20	261.95	0.75	0.030	4.7	14	296	1668
zona con abundante pirita	261.95	262.35	0.40	0.790	209.2	554	751	3657
vetilla con sulfuros	268.40	269.45	1.05	0.050	7	48	131	455
zona con abundante pirita	269.45	270.10	0.65	0.076	2.6	8	42	160
	299.50	300.30	0.80	0.090	5.9	121	63	119
	300.30	301.10	0.80	0.015	2.3	18	32	123
	301.10	301.90	0.80	0.065	10.5	610	57	123
	301.90	302.40	0.50	0.042	1.4	17	26	77
	25.25	27.15	1.90	0.015	2.9	325	48	206
	27.15	28.05	0.90	0.015	0.9	26	23	118
	28.05	28.95	0.90	0.005	2.2	26	27	122

## Guadalupe Vein (GPE)

<b>NS-07-01</b> <i>Bearing 021 Dip -45 - Length 209.35 m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Host rock with weak fine disse	19.00	20.00	1.00	<0.005	<0.1	5	19	96
Host rock with weak fine disse	20.00	21.00	1.00	<0.005	<0.1	5	21	89
Host rock with weak fine disse	21.00	22.00	1.00	<0.005	<0.1	6	15	66
Host rock with weak fine disse	22.00	23.00	1.00	<0.005	<0.1	7	17	66
Host rock with weak fine disse	59.60	60.60	1.00	<0.005	1.7	13	694	3635
Veta Guadalupe	200.70	201.55	0.85	0.171	18.2	190	634	751
Strong diss pyrite	180.65	181.35	0.70	<0.005	7.4	19	4814	1829

## La Estela vein (LE)

<b>LE-06-03</b> <i>Bearing 185 - Dip - 45 - Length 251.85 m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
	90.35	91.35	1.00	<0.005	8.40	0.005	506	652
white quartz vein	91.35	91.80	0.45	<0.005	22.3	0.013	521	15000
	91.80	92.80	1.00	<0.005	1.5	0.002	121	540
	92.80	93.40	0.60	<0.005	0.6	0.003	49	192
	93.40	94.40	1.00	0.02	0.5	0.003	52	207
	94.40	95.40	1.00	<0.005	0.3	0.002	23	141
	95.40	96.45	1.05	<0.005	0.1	0.002	22	172
	96.45	97.45	1.00	<0.005	0.4	0.004	44	150
	97.45	98.45	1.00	<0.005	1.1	0.005	34	242
	98.45	99.50	1.05	<0.005	0.1	0.005	44	197
	99.50	100.50	1.00	<0.005	<0.1	0.005	32	132
	100.50	101.50	1.00	<0.005	0.4	0.005	32	138
	217.60	218.60	1.00	<0.005	0.4	0.002	103	225
	218.60	219.60	1.00	<0.005	<0.1	0.002	74	153
	219.60	220.65	1.05	0.04	4.1	0.004	86	183
	220.65	221.85	1.20	0.03	1.1	0.005	113	379
White quartz vein (true vein), La Estela vein	221.85	222.85	1.00	<b>1.37</b>	<b>132.1</b>	0.020	746	1417
	222.85	223.70	0.85	0.24	18.4	0.004	104	199
	223.70	224.70	1.00	<0.005	0.1	0.004	31	84
	224.70	225.70	1.00	<0.005	<0.1	0.004	178	442
	225.70	226.75	1.05	0.02	4.7	0.010	3096	3837
Wh qtz veinlets (less than 1- cm wide) along core axes. Ore mineralogy consists mainly of	246.25	247.05	0.80	<b>4.01</b>	<b>107.3</b>	0.821	19300	40500
	247.05	248.10	1.05	0.42	36	0.300	3627	2877
	248.10	249.40	1.30	0.29	19.3	0.059	5273	17500

<b>LE-06-02</b> <i>Bearing 215 - Dip -45 - Length 236.25 m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
	209.95	211.00	1.05	<0.005	<0.1	0.002	0.004	0.010
	211.00	212.00	1.00	<0.005	0.1	0.002	0.005	0.011
	212.00	213.00	1.00	<0.005	<0.1	0.002	0.004	0.009
	213.00	214.05	1.05	0.02	5.5	0.002	0.011	0.020
	214.05	215.05	1.00	0.17	21.6	0.002	0.017	0.044
Footwall La Estela vein	215.05	216.00	0.95	<b>0.869</b>	<b>52.5</b>	0.006	0.008	0.015
	216.05	217.10	1.05	0.025	9.0	0.007	0.048	0.081
	217.10	218.10	1.00	0.015	14.8	0.007	0.033	0.046
	218.10	218.60	0.50	0.052	18.0	0.016	0.099	0.091
Hangingwall La Estela vein	218.60	219.10	0.50	<b>3.95</b>	<b>1744.1</b>	0.946	2.460	0.550
	59.85	60.85	1.00	0.025	13.0	0.009	0.016	0.009
	60.85	61.85	1.00	<0.005	1.2	0.003	0.006	0.010
	61.85	62.90	1.05	<0.005	0.6	0.003	0.005	0.015
	62.90	63.90	1.00	<0.005	1.6	0.002	0.008	0.021
	63.90	64.90	1.00	<0.005	1.4	0.002	0.010	0.026
	64.90	65.95	1.05	<0.005	2.9	0.002	0.028	0.036
	65.95	66.95	1.00	<0.005	4.0	0.002	0.045	0.080
	66.95	67.95	1.00	<0.005	0.4	0.004	0.005	0.008
	67.95	69.00	1.05	<0.005	0.4	0.009	0.002	0.007
	69.00	70.00	1.00	<0.005	0.9	0.003	0.003	0.027
	94.65	95.65	1.00	<0.005	2.0	0.003	0.005	0.018
	95.65	96.65	1.00	<0.005	1.3	0.002	0.007	0.035
	96.65	97.70	1.05	<0.005	2.1	0.003	0.010	0.031
	97.70	98.70	1.00	<0.005	2.7	0.003	0.005	0.031

	98.70	99.70	1.00	0.015	2.7	0.003	0.005	0.011
	99.70	100.75	1.05	0.01	3.3	0.002	0.005	0.014
	100.75	101.75	1.00	<0.005	2.3	0.002	0.006	0.023
	101.75	102.75	1.00	<0.005	1.1	0.002	0.004	0.010
	102.75	103.80	1.05	<0.005	0.4	0.002	0.005	0.019
	103.80	104.80	1.00	<0.005	0.4	0.001	0.001	0.015

<b>LE-06-01 Bearing 220 - Dip -45 - Length 200.6m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Diss py + silicif	185.40	186.40	1.00	<0.005	<0.1	36	21	69
White quartz vein	186.40	186.65	0.25	0.03	14.5	60	1240	3120
Diss py + silicif	186.65	187.65	1.00	<0.005	<0.1	25	60	137
Diss py + silicif	69.30	70.30	1.00	<0.005	2.4	32	181	404
Diss py + silicif	70.30	71.30	1.00	<0.005	11.4	64	469	1160
Diss py + silicif	71.30	72.35	1.05	<0.005	2	28	175	517
Diss py + silicif	72.35	73.35	1.00	0.015	0.8	22	60	180
Diss py + silicif	73.35	74.35	1.00	<0.005	0.9	38	38	152
Diss py + silicif	74.35	75.40	1.05	0.01	2.4	39	57	183
Diss py + silicif	86.55	87.60	1.05	<0.005	9.4	82	370	526
Diss py + silicif	87.60	88.60	1.00	0.03	1.4	62	34	145
Diss py + silicif	88.60	89.60	1.00	<0.005	1.1	59	46	127
Diss py + silicif	89.60	90.60	1.00	0.01	1.9	46	50	179
Diss py + silicif	90.60	91.65	1.05	0.01	0.2	41	25	95
Diss py + silicif	91.65	92.65	1.00	<0.005	<0.1	60	30	86
Diss py + silicif	92.65	93.70	1.05	0.053	0.6	66	33	140
Diss py + silicif	93.70	94.70	1.00	<0.005	1.4	73	56	177
Diss py + silicif	94.70	95.70	1.00	<0.005	0.2	70	39	121
Diss py + silicif	95.70	96.75	1.05	<0.005	1	92	37	120
Diss py + silicif	96.75	97.75	1.00	0.01	2	63	79	251
Diss py + silicif	97.75	98.75	1.00	0.01	1.7	57	31	195

## Los Angeles zone (LA)

<b>LA-07-05 Bearing 201 Dip -45 Length 149.8m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Strong diss pyrite	95.80	96.60	0.80	0.093	54.4	1836	806	1300
Quartz veining	99.80	100.15	0.35	0.992	87	103	248	337
Quartz veining	100.15	100.55	0.40	0.040	5.3	10	79	273
Los Angeles vein	100.55	101.25	0.70	0.418	174.2	304	2563	13500
Los Angeles vein	101.25	101.95	0.70	0.234	17.8	59	219	491
Quartz veining	104.55	105.55	1.00	0.143	3.2	4	36	572
Quartz veining	106.75	107.45	0.70	0.035	5.3	15	34	242
Quartz veining	111.40	112.35	0.95	0.025	3.5	31	29	103
Quartz veining	112.35	113.45	1.10	0.025	2	7	81	493
Quartz veining	113.45	114.15	0.70	0.095	12	34	646	2662

<b>LA-07-04 Bearing 225 Dip -44 Length 115.25m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Silicification + pyrite	87.95	88.30	0.35	0.005	0.9	7	91	269
Fault- contact zone	100.70	101.70	1.00	0.404	48.8	48	402	2189
Los Angeles vein	101.70	102.80	1.10	0.630	606.9	555	1277	3660
Los Angeles vein	102.80	103.80	1.00	0.373	45.3	35	470	589
Los Angeles vein	103.80	104.75	0.95	0.149	20.9	36	258	403
Los Angeles vein	104.75	105.80	1.05	0.344	67.9	42	285	589
Los Angeles vein	105.80	106.80	1.00	0.830	527.6	210	2519	7532
Los Angeles vein	106.80	107.40	0.60	0.329	168.5	78	1103	2762
Wh qtz veining w/diss fine pyri	107.40	108.50	1.10	0.057	17.3	54	242	831
Wh qtz veining w/diss fine pyri	108.50	109.10	0.60	0.121	13.5	37	249	679

<b>LA-07-03 Bearing 214 Dip -70 Length 140.4m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Fault zone	120.50	121.30	0.80	0.115	12.5	32	558	1027
Wall rock	121.30	122.30	1.00	0.030	3	48	275	8623
Wh qtz veining	122.30	123.30	1.00	0.045	13.2	35	430	3316
Wh qtz veining	123.30	124.30	1.00	0.130	59.7	135	1994	15800
Wall rock	124.30	125.40	1.10	0.020	8.1	127	416	1655
Wall rock	125.40	126.50	1.10	<.005	2.3	98	255	592

Wh qtz veining	126.50	127.10	0.60	0.010	2.8	37	465	1686
Wh qtz veining	127.10	127.75	0.65	0.040	43.1	602	2952	26000
Wall rock	127.75	128.75	1.00	0.025	18.4	182	630	4138
Wall rock	128.75	129.75	1.00	0.035	13.7	92	2646	3206
Wall rock	129.75	130.35	0.60	0.020	3.3	72	298	3062
Los Angeles vein	130.35	131.30	0.95	0.319	59.1	1143	1330	3580
Wall rock	131.30	132.15	0.85	0.015	1	26	216	582
Los Angeles vein	132.15	132.30	0.15	1.783	71.2	445	64200	60000

<b>LA-07-02 Bearing 215 Dip -45 Length 185.3m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
White quartz veinlet w/sulfides	95.30	98.35	3.05	0.058	9.4	54	1124	2523
White quartz veinlet w/sulfides	98.35	99.35	1.00	0.115	101.9	57	609	898
Quartz veining zone	99.35	100.35	1.00	0.085	10.2	14	70	260
Los Angeles vein w/sulfides	100.35	101.35	1.00	0.052	15.5	9	76	356
Quartz veining zone	101.35	102.35	1.00	0.015	3.3	9	301	644
Quartz veining zone	102.35	103.35	1.00	0.085	7.2	35	259	849
Los Angeles vein w/sulfides	103.35	104.35	1.00	0.480	45.5	49	229	487
Strong pyrite and silicification	104.35	105.35	1.00	0.125	34.9	43	412	1670
	105.35	106.35	1.00	1.280	40.7	62	176	309

<b>LA-07-01 Bearing 32 Dip -44 Length 358.9m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Wh qtz veinlet w/diss sulfides	136.45	136.80	0.35	0.959	57.4	57	424	283
Wh qtz veinlet w/diss sulfides	157.10	158.10	1.00	0.135	8.7	122	3506	6087
Qtz veining zone	326.70	327.25	0.55	0.025	2.3	11	223	468
Los Angeles vein w/sulfides	327.25	327.55	0.30	13.645	711.9	5602	8259	4220
Qtz veining zone	327.55	328.35	0.80	0.368	5.5	141	1192	1490
Qtz veining zone	328.35	329.25	0.90	0.044	1.1	29	317	1217
Los Angeles vein w/sulfides	329.25	329.65	0.40	0.649	168.7	3346	61700	59000
Silicification and strong pyrite	329.65	330.05	0.40	0.047	2.9	93	500	595

## Nuestra Senora (NS)

<b>NS-07-05 Bearing 186 Dip -45 Length 124.85m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
zona de ramaleo con piritita	61.05	61.75	0.70	0.195	27.4	126	1115	245
zona de ramaleo con piritita	61.45	62.45	1.00	0.115	19.6	49	1485	600
zona de ramaleo con piritita	62.45	63.15	0.70	0.150	58.9	314	1189	337
zona de vetilleo con hilos de piritita	96.20	97.10	0.90	0.239	3.1	228	864	2272
zona de vetilleo con hilos de piritita	97.10	97.70	0.60	0.14	7.9	185	3755	3406
zona de vetilleo con hilos de piritita	97.70	98.40	0.70	0.109	11.7	152	1066	2392
zona abundante de piritita	98.40	99.00	0.60	<0.005	0.1	10	207	3192

<b>NS-07-04 Bearing 162 Dip -45 Length 101.6m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
zona de ramaleo con cuarzo y piritita	68.90	69.55	0.65	0.115	38.8	1669	2968	1429
zona de ramaleo con cuarzo y piritita	69.55	70.10	0.55	0.050	4.7	155	708	810
zona con abundante piritita	72.60	73.40	0.80	0.025	3.6	482	214	484
zona con abundante piritita	75.35	76.00	0.65	0.032	5.2	15	638	243
zona de ramaleo de cuarzo	88.45	89.15	0.70	<0.005	0.4	4	63	343
zona de ramaleo de cuarzo	89.13	89.85	0.72	<0.005	14.6	684	332	1110
zona de ramaleo de cuarzo	89.85	90.55	0.70	0.005	8.5	88	307	539
zona de ramaleo de cuarzo	90.55	91.25	0.70	0.02	53.9	225	518	1213
zona de ramaleo de cuarzo	91.25	91.90	0.65	0.01	22	50	763	1335
zona de veta de Nuestra Señora	91.90	92.90	1.00	0.03	146	233	829	2262
zona de veta de Nuestra Señora	92.90	93.40	0.50	0.015	196.5	578	1728	3321
zona de veta de Nuestra Señora	93.40	94.15	0.75	0.065	103.4	875	14800	15300
zona de ramaleo de cuarzo	94.15	95.05	0.90	0.015	9.6	53	3799	1223
zona de ramaleo de cuarzo	95.05	95.85	0.80	0.01	5.2	19	590	1338
zona de ramaleo de cuarzo	95.85	96.95	1.10	<0.005	0.5	4	268	1490

<b>NS-07-01 Bearing 330 Dip -45 Length 167.1m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
zona con abundante con hilos de piritita	98.20	98.75	0.55	0.025	0.9	14	440	1625

zona con abundante con hilos	98.75	99.40	0.65	0.010	1.7	12	964	2162
veta de cuarzo blanco con piritita	99.40	99.85	0.45	0.045	258.2	7184	65500	77800
zona con abundante piritita	99.85	100.20	0.35	0.085	14	312	3654	19600
zona con abundante piritita	100.20	100.90	0.70	<0.005	<0.1	11	289	585
zona con abundante piritita	100.90	101.90	1.00	<0.005	0.1	19	244	889
zona con abundante piritita	101.90	102.90	1.00	<0.005	<0.1	3	51	624
zona de vetilleo con calcopiritita	159.90	161.05	1.15	3.291	53.6	14700	157	661
zona de vetilleo con calcopiritita	161.05	161.95	0.90	1.195	33.8	8469	133	359
zona de vetilleo con calcopiritita	161.95	163.55	1.60	<0.005	<0.1	50	17	249
zona de vetilleo con calcopiritita	163.55	164.70	1.15	0.380	19.8	5493	72	403

## San Jose zone (SJ)

<b>SJ-07-01</b>								
<i>Bearing - Dip - Length m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Argillized + strong fine grain dis	31.75	33.25	1.50	<0.005	<0.1	7	32	88
Argillized + strong fine grain dis	33.25	34.75	1.50	<0.005	<0.1	24	21	94
Argillized + strong fine grain dis	34.75	36.25	1.50	<0.005	<0.1	18	21	102
Argillized + strong fine grain dis	36.25	37.75	1.50	<0.005	<0.1	9	26	64
Argillized + strong fine grain dis	37.75	39.25	1.50	<0.005	<0.1	11	19	82
Argillized + strong fine grain dis	39.25	40.75	1.50	<0.005	<0.1	15	17	68
Argillized + strong fine grain dis	40.75	42.25	1.50	<0.005	<0.1	13	19	65
Argillized + strong fine grain dis	42.25	43.75	1.50	<0.005	<0.1	11	19	56
Argillized + strong fine grain dis	43.75	45.25	1.50	<0.005	<0.1	8	18	49
Argillized + strong fine grain dis	45.25	46.75	1.50	<0.005	<0.1	21	18	74
Argillized + strong fine grain dis	46.75	48.25	1.50	<0.005	<0.1	9	19	76
Argillized + strong fine grain dis	57.85	58.65	0.80	<0.005	<0.1	8	17	75
Argillized + strong fine grain dis	58.65	59.55	0.90	<0.005	<0.1	10	24	68
Argillized + strong fine grain dis	110.30	111.80	1.50	<0.005	0.2	25	26	172
Argillized + strong fine grain dis	111.80	113.30	1.50	<0.005	0.1	12	22	142
Argillized + strong fine grain dis	113.30	114.80	1.50	<0.005	0.2	10	21	149
Argillized + strong fine grain dis	114.80	116.30	1.50	0.015	0.3	9	14	75
Argillized + strong fine grain dis	116.30	117.80	1.50	0.020	0.8	15	57	451
Argillized + strong fine grain dis	117.80	119.30	1.50	<0.005	1.3	18	159	1146
Argillized + strong fine grain dis	119.30	120.80	1.50	<0.005	1.3	16	129	713
Argillized + strong fine grain dis	120.80	122.30	1.50	0.165	0.7	15	83	512
Argillized + strong fine grain dis	122.30	123.80	1.50	<0.005	0.5	14	47	329
Argillized + strong fine grain dis	123.80	125.30	1.50	0.025	0.5	22	99	628
Argillized + strong fine grain dis	125.30	126.80	1.50	0.010	1	21	132	711
Argillized + strong fine grain dis	126.80	128.30	1.50	0.010	1.3	16	53	311
Argillized + strong fine grain dis	128.30	129.80	1.50	<0.005	0.8	6	49	464
Argillized + strong fine grain dis	129.8	131.3	1.5	0.005	0.4	15	29	170
Argillized + strong fine grain dis	131.3	132.8	1.5	0.010	<0.1	14	33	142
Argillized + strong fine grain dis	132.8	134.3	1.5	0.035	<0.1	19	53	159
Argillized + strong fine grain dis	134.3	136.6	2.3	0.020	0.5	14	45	181
Argillized + strong fine grain dis	136.6	137.8	1.2	0.015	4.6	7	30	163
Argillized + strong fine grain dis	137.8	138.8	1	<0.005	29	26	79	160
Argillized + strong fine grain dis	138.8	140.3	1.5	0.045	7.4	14	39	154
Argillized + strong fine grain dis	140.3	140.9	0.6	0.030	2.4	15	16	70
Argillized + strong fine grain dis	140.9	142.9	2	0.025	1.9	9	9	40

<b>SJ-06-02</b>								
<i>Bearing 0 - Dip -60 - Length 373.7m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
	94.00	95.00	1.00	<0.005	<0.1	16	22	140
	95.00	96.00	1.00	<0.005	<0.1	26	31	125
	97.00	97.00	1.00	<0.005	<0.1	21	34	289
	98.00	98.00	1.00	<0.005	0.2	29	38	836
	99.00	99.00	1.00	<0.005	<0.1	36	42	280
	100.00	100.00	1.00	<0.005	0.5	42	57	661
	101.00	101.00	1.00	<0.005	2.2	35	40	1251
	102.00	102.00	1.00	<0.005	8.5	48	878	2280
	103.00	103.00	1.00	0.035	5.5	81	196	840
	104.00	104.00	1.00	0.015	4.4	36	75	1007
	105.00	105.00	1.00	<0.005	8.3	46	388	1691
	106.00	106.00	1.00	<0.005	5.9	66	370	1802
	107.00	107.00	1.00	0.01	3.8	56	118	856
	108.00	108.00	1.00	0.005	2.7	45	56	766
	136.20	137.20	1.00	<0.005	2.5	21	58	581
	137.20	138.20	1.00	<0.005	2	23	46	416
	138.20	139.20	1.00	<0.005	<0.1	16	42	134

	139.20	140.20	1.00	<0.005	<0.1	16	42	83
	140.20	141.20	1.00	<0.005	<0.1	10	36	63
	141.20	142.20	1.00	<0.005	<0.1	9	32	67
	142.20	143.20	1.00	<0.005	<0.1	16	32	116
	143.20	144.20	1.00	<0.005	<0.1	10	35	45
	144.20	145.20	1.00	<0.005	<0.1	21	30	79
	145.20	146.20	1.00	<0.005	<0.1	25	27	155
	146.20	147.20	1.00	<0.005	<0.1	15	31	173
	147.20	148.20	1.00	<0.005	<0.1	18	44	314
	148.20	149.20	1.00	<0.005	0.4	20	159	499
	149.20	150.20	1.00	<0.005	0.4	14	166	623
	150.20	151.20	1.00	<0.005	0.4	18	90	328
	151.20	267.40	1.00	<0.005	<0.1	7	65	114
	267.40	268.40	1.00	<0.005	<0.1	10	18	63
	268.40	269.40	1.00	<0.005	<0.1	7	17	63
	269.40	270.40	1.00	<0.005	<0.1	19	24	64
	270.40	271.40	1.00	<0.005	<0.1	8	12	69
	271.40	272.40	1.00	<0.005	<0.1	10	16	68
	272.40	273.40	1.00	<0.005	<0.1	12	15	64
	273.40	274.40	1.00	<0.005	<0.1	7	11	39
	274.40	275.40	1.00	<0.005	<0.1	7	15	59
	275.40	276.40	1.00	<0.005	<0.1	10	19	57
	276.40	277.40	1.00	<0.005	<0.1	18	34	118
	277.40	278.40	1.00	<0.005	<0.1	8	38	100
	278.40	279.40	1.00	<0.005	<0.1	13	42	178
	279.40	280.40	1.00	<0.005	<0.1	16	65	175
	280.40	281.40	1.00	<0.005	<0.1	10	14	55
	281.40	282.40	1.00	<0.005	<0.1	11	28	87
	282.40	351.70	1.00	<0.005	<0.1	24	19	69
	351.70	352.70	1.00	<0.005	2.2	19	157	601
	352.70	353.70	1.00	0.020	1.7	9	159	347
	353.70	354.40	0.70	0.010	2.5	15	719	1879
	354.40	354.80	0.40	0.030	16.9	21	8696	988
	354.80	355.95	1.15	0.045	0.7	9	411	1612
	355.95	357.10	1.15	0.050	2.2	20	590	2427
	357.10	357.70	0.60	0.425	93.3	37	2210	5815

<b>SJ-06-01 Bearing 0 - Dip -60 - Length 373.7m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
	239.95	240.95	1.00	0.04	2.3	33	119	227
	240.95	241.95	1.00	0.07	4.4	540	106	773
	241.95	243.00	1.05	<0.005	0.4	118	51	161
	243.00	244.00	1.00	<0.005	<0.1	47	25	170
	244.00	245.00	1.00	<0.005	<0.1	74	49	164
	245.00	246.05	1.05	0.06	1.3	450	278	1956
	246.05	247.05	1.00	<0.005	<0.1	61	46	189
	247.05	248.05	1.00	<0.005	<0.1	41	48	188
	248.05	249.10	1.05	<0.005	<0.1	41	26	177
	249.10	250.10	1.00	<0.005	<0.1	92	35	295
	250.10	251.10	1.00	<0.005	<0.1	181	46	339
	251.10	252.15	1.05	0.02	<0.1	53	67	452
	252.15	253.15	1.00	<0.005	<0.1	25	28	434
	253.15	253.90	0.75	<0.005	<0.1	29	35	384
	253.90	254.90	1.00	<0.005	<0.1	42	17	106
	254.90	255.90	1.00	<0.005	<0.1	57	29	103
	255.90	256.95	1.05	0.01	<0.1	28	152	228
	256.95	257.95	1.00	0.01	<0.1	68	51	119
	257.95	258.95	1.00	<0.005	<0.1	60	34	98
	258.95	260.00	1.05	<0.005	<0.1	37	24	47
	260.00	261.00	1.00	<0.005	<0.1	49	21	89
	261.00	262.00	1.00	<0.005	<0.1	67	22	72
	262.00	263.05	1.05	<0.005	<0.1	45	39	105
	263.05	264.05	1.00	<0.005	<0.1	25	32	143
	264.05	265.05	1.00	0.015	1.8	46	56	176
	265.05	266.10	1.05	0.01	<0.1	71	41	196
	266.10	267.10	1.00	<0.005	<0.1	41	36	174
	267.10	268.10	1.00	0.01	0.3	98	34	408
	268.10	269.15	1.05	<0.005	0.2	35	39	128
	269.15	270.15	1.00	<0.005	0.3	55	37	109
	270.15	271.15	1.00	<0.005	0.4	54	46	50
	271.15	272.20	1.05	<0.005	<0.1	42	30	38
	272.20	273.20	1.00	<0.005	<0.1	46	50	98
	273.20	274.20	1.00	<0.005	<0.1	44	32	77

	274.20	275.25	1.05	<0.005	<0.1	46	33	342
	51.15	52.15	1.00	<0.005	0.2	18	21	164
	52.15	54.45	2.30	0.02	2.3	18	324	331
	54.45	55.45	1.00	<0.005	2.4	21	50	188
	55.45	56.45	1.00	<0.005	1.6	28	49	120

## San Luis zone (SL)

<b>SL-06-01</b>								
<i>Bearing 0 - Dip 90 - Length 219.15 m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu g/t		
Intrusive with py+spec and rare	111.80	112.80	1.00	0.03	0.7	516		
Intrusive with py+spec and rare	112.80	113.80	1.00	<0.005	<0.1	27		
Intrusive with py+spec and rare	113.80	114.85	1.05	0.05	1.1	191		
Intrusive with py+spec and rare	114.85	115.85	1.00	0.03	6.3	416		
Intrusive with py+spec and rare	115.85	116.85	1.00	0.02	7.5	844		
Intrusive with py+spec and rare	116.85	117.90	1.05	0.07	5.8	809		
Intrusive with py+spec and rare	117.90	118.70	0.80	0.05	2.3	708		
Intrusive with py+spec and rare	118.70	119.80	1.10	0.38	13.9	654		
Intrusive with py+spec and rare	119.80	121.75	1.10*	0.04	8.5	2271		
Intrusive with py+spec and rare	121.75	124.80	1.20*	0.05	7.2	2724		
Intrusive with py+spec and rare	124.80	125.80	1.00	0.04	0.8	705		
Intrusive with py+spec and rare	125.80	126.80	1.00	0.08	7.4	2239		
Intrusive with py+spec and rare	126.80	127.85	0.85*	0.07	1.7	977		
Intrusive with py+spec and rare	127.85	128.85	1.00	0.03	1.5	989		
Intrusive with py+spec and rare	128.85	129.85	1.00	0.02	1.5	772		
Fault zone from 130.70m to 13	129.85	130.90	1.05	0.04	2.1	918		
AVINO VEIN	130.90	131.90	1.00	<b>0.89</b>	5.2	224		
AVINO VEIN	131.90	132.90	1.00	<b>1.87</b>	38.2	713		
AVINO VEIN	132.90	133.95	1.05	<b>1.03</b>	<b>48.6</b>	693		
AVINO VEIN	133.95	134.95	1.00	<b>3.44</b>	<b>80.4</b>	356		
AVINO VEIN	134.95	135.95	1.00	<b>0.55</b>	<b>60.7</b>	873		
AVINO VEIN	135.95	137.00	0.70*	<b>0.35</b>	43.9	2024		
AVINO VEIN	137.00	140.00	1.20*	<b>0.52</b>	<b>90.1</b>	1822		
AVINO VEIN	140.00	141.05	1.05	<b>0.19</b>	32.0	3541		
AVINO VEIN	141.05	142.05	1.00	<b>0.88</b>	<b>96.3</b>	23000		
AVINO VEIN	142.05	143.10	0.60*	<b>3.66</b>	40.0	1285		
AVINO VEIN	143.10	144.10	1.00	<b>1.65</b>	18.5	1076		
AVINO VEIN	144.10	145.10	1.00	<b>1.84</b>	10.8	3164		
AVINO VEIN	145.10	146.15	1.05	<b>4.21</b>	28.9	5279		
AVINO VEIN	146.15	147.15	1.00	<b>1.64</b>	17.9	1291		
AVINO VEIN	147.15	148.14	0.99	<b>1.93</b>	18.8	573		
AVINO VEIN	148.14	149.20	1.06	<b>2.33</b>	5.4	531		
AVINO VEIN	149.20	150.20	1.00	<b>1.95</b>	12.0	1947		
AVINO VEIN	150.20	150.90	0.70	<b>1.10</b>	<b>51.8</b>	4457		
AVINO VEIN	150.90	151.90	1.00	<b>0.85</b>	39.3	9511		
AVINO VEIN	151.90	152.90	1.00	<b>0.75</b>	23.9	3518		
AVINO VEIN	152.90	153.95	1.05	<b>1.48</b>	28.1	4084		
AVINO VEIN	153.95	154.95	1.00	<b>0.62</b>	15.1	1830		
AVINO VEIN	154.95	155.95	1.00	0.34	22.0	3068		
Intrusive Rock with weak py+m	155.95	157.00	1.05	0.02	0.3	493		
Intrusive Rock with weak py+m	157.00	158.00	1.00	<0.005	0.4	681		
Intrusive Rock with weak py+m	158.00	159.00	1.00	<0.005	0.4	346		
Intrusive Rock with weak py+m	159.00	160.05	1.05	<0.005	<0.1	29		
Intrusive Rock with weak py+m	160.05	161.05	1.00	<0.005	<0.1	41		
Intrusive Rock with weak py+m	161.05	162.05	1.00	<0.005	<0.1	112		
Intrusive Rock with weak py+m	162.05	163.10	1.05	<0.005	<0.1	17		
Intrusive Rock with weak py+m	163.10	164.10	1.00	<0.005	<0.1	25		
Intrusive Rock with weak py+m	164.10	165.10	1.00	<0.005	<0.1	13		
Intrusive Rock with weak py+m	165.10	166.15	1.05	<0.005	<0.1	13		
Intrusive Rock with weak py+m	166.15	167.15	1.00	<0.005	<0.1	111		
Intrusive Rock with weak py+m	167.15	168.00	0.85	0.025	0.1	20		
Intrusive Rock with weak py+m	168.00	169.20	1.20	0.035	<0.1	20		

## San Pedro & Paulo Zones (SP&P)

<b>SP&amp;P-07-01</b>								
<i>Bearing 328 Dip -45 Length 181.25m</i>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
vetila de cuarzo con diss pyrita	41.45	41.80	0.35	0.080	<b>131.2</b>	8460	3397	2143
vetila de cuarzo con diss pyrita	41.80	42.80	1.00	0.020	13.9	543	1417	3634

vetila de cuarzo con diss pyrita	42.80	43.80	1.00	<0.005	6.3	133	951	1110
vetila de cuarzo con diss pyrita	43.80	44.80	1.00	0.030	26.3	387	720	732
vetila de cuarzo con diss pyrita	44.80	45.70	0.90	0.105	54.0	589	511	506
vetila de cuarzo con diss pyrita	45.70	46.50	0.80	<0.005	4.5	79	490	2292
vetila de cuarzo con diss pyrita	46.50	47.85	1.35	<0.005	1.9	12	327	1780
vetila de cuarzo con diss pyrita	47.85	48.65	0.80	<0.005	1.3	10	118	886
vetila de cuarzo con diss pyrita	48.65	49.45	0.80	0.005	1.2	9	455	1195
vetila de cuarzo con diss pyrita	49.45	50.25	0.80	0.06	14.3	209	2941	5368
	94.00	95.20	1.20	0.01	3.4	37	358	1481
	95.20	96.40	1.20	<0.005	1.2	15	141	704
	96.40	97.60	1.20	<0.005	0.8	7	140	548
	97.60	98.80	1.20	<0.005	1.7	5	88	369
	98.80	100.00	1.20	<0.005	1.2	25	246	988
	100.00	101.20	1.20	<0.005	0.7	5	179	477
	101.20	102.40	1.20	<0.005	0.4	2	72	257
	102.40	103.60	1.20	<0.005	0.3	1	63	138
	103.60	104.80	1.20	<0.005	0.3	2	52	151
	104.80	106.00	1.20	<0.005	0.5	2	79	135
	106.00	107.20	1.20	<0.005	1.5	24	123	385
	107.20	108.40	1.20	0.01	3.1	28	116	105
	108.40	109.60	1.20	<0.005	1.3	20	67	274
	124.00	125.20	1.20	<0.005	0.3	7	41	120
	125.20	126.40	1.20	<0.005	0.4	10	21	44
	126.40	127.60	1.20	<0.005	0.3	9	56	157
	127.60	128.80	1.20	<0.005	0.3	10	66	185
	128.80	130.00	1.20	<0.005	0.3	10	46	503
	130.00	131.20	1.20	0.02	0.3	14	44	353
	131.20	132.20	1.00	<0.005	0.4	14	64	910
	137.55	138.25	0.70	<0.005	1.1	19	233	1354
	138.25	138.90	0.65	<0.005	1.3	6	200	1162
	138.90	139.55	0.65	0.01	10.0	107	519	2565
	139.55	140.20	0.65	0.05	133.0	864	118	418
	140.20	141.20	1.00	0.015	2.2	97	267	2067
	141.20	142.00	0.80	<0.005	1.0	29	317	1131
	142.00	142.40	0.40	0.01	31.2	219	572	3020

## Santa Ana zone (STA)

<b>STA-07-01 Bearing 65 Dip -50 Length 315.3m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
zona con abundante pirita	15.70	16.60	0.90	0.020	1.1	14	63	180
zona con abundante pirita	50.50	51.70	1.20	<0.005	0.3	6	133	621
zona con abundante pirita	51.70	52.95	1.25	0.085	16.6	14	612	948
vetilla con sulfuros	52.95	53.55	0.60	<0.005	0.1	7	94	1120
zona con abundante pirita	53.55	54.55	1.00	<0.005	<0.1	5	76	515
zona con abundante pirita	54.55	55.55	1.00	<0.005	<0.1	9	63	239
veta Santa Ana	89.90	90.95	1.05	0.03	4.1	40	1134	2490
veta Santa Ana	90.95	91.85	0.90	0.095	11.2	108	2810	10200
veta Santa Ana	91.85	92.40	0.55	0.09	18	79	6163	31300
zona de silificacion	99.00	100.10	1.10	<0.005	1.4	8	169	394
zona de silificacion	100.10	101.05	0.95	<0.005	0.4	6	114	362
zona de silificacion	101.05	102.05	1.00	<0.005	0.2	6	58	122
zona de silificacion	102.05	103.05	1.00	<0.005	0.2	4	40	226
zona de silificacion	103.05	104.10	1.05	<0.005	0.2	5	83	57
zona de silificacion	104.10	105.10	1.00	<0.005	0.2	3	44	173
vetilla con sulfuros	141.15	141.45	0.30	0.06	17.3	57	1199	5983
zona con abundante pirita	221.45	222.55	1.10	0.040	2.3	43	1117	1283
zona de ramaleo	227.20	227.55	0.35	0.020	9.7	468	2452	1359
zona con abundante pirita	227.55	228.75	1.20	<0.005	6	617	1550	818
vetilla con sulfuros	228.75	229.05	0.30	0.325	82.4	5326	>10000	2110
	229.05	230.15	1.10	0.005	2	112	1186	1503
zona con abundante pirita	230.15	230.95	0.80	0.02	8.4	968	1782	823
zona con abundante pirita	230.95	231.85	0.90	0.01	5.5	285	2299	972

## Santiago vein (ST)

<b>ST-07-09 Bearing - Dip - Length m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
vetilla de cuarzo blanco	137.20	137.60	0.40	0.075	10.4	263	246	337

vetilleo al hilo	137.60	138.40	0.80	0.035	6.5	142	618	1871
zona abundante de pirita	138.40	139.40	1.00	0.105	9.8	156	918	233
Santiago Vein	139.40	140.40	1.00	0.283	30.2	663	1604	232
zona de tepetate	140.40	141.70	1.30	0.025	8.6	396	462	382
zona de vetilleo	141.70	142.20	0.50	0.035	11.4	572	1291	2054
vetilla de cuarzo blanco	152.15	152.45	0.30	0.025	1.7	17	116	289

<b>ST-07-08 Bearing - Dip - Length m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
vetilleo al hilo con sulfuros	76.15	76.50	0.35	2.381	1724.6	228	1973	2903
veta con sulfuros	86.20	86.80	0.60	0.151	116.8	290	1051	3021
zona abundante de pirita	86.80	87.60	0.80	0.354	10.1	41	309	343
zona abundante de pirita	87.60	88.40	0.80	0.035	4.9	11	161	349
zona abundante de pirita	88.40	89.20	0.80	0.015	7.4	61	219	300
zona abundante de pirita	89.20	90.00	0.80	0.105	30.5	325	701	520
zona abundante de pirita	90.00	90.80	0.80	0.053	8.8	364	137	224
zona abundante de pirita	90.80	91.60	0.80	0.052	7.9	185	163	185
zona abundante de pirita	91.60	92.40	0.80	0.079	9.1	127	107	410
zona abundante de pirita	92.40	93.50	1.10	0.095	5.1	78	77	390
veta Santiago con sulfuros	93.50	94.20	0.70	0.305	15.7	147	936	475
zona abundante de pirita	94.20	95.00	0.80	0.045	10.3	84	230	313
zona abundante de pirita	95.00	95.80	0.80	0.035	7.3	35	207	509
zona abundante de pirita	95.80	96.60	0.80	0.020	7	67	141	335
zona abundante de pirita	96.60	97.40	0.80	0.025	5.1	65	244	399
zona abundante de pirita	97.40	98.20	0.80	0.038	10.5	40	3531	7907
zona abundante de pirita	98.20	99.00	0.80	0.042	9.5	125	1623	2435
zona abundante de pirita	99.00	99.60	0.60	0.046	5.2	51	165	875
Santiago vein	99.60	100.10	0.50	0.694	48.7	105	882	1306
zona abundante de pirita	100.10	100.90	0.80	0.081	17.7	551	1762	1697
zona abundante de pirita	100.90	101.70	0.80	0.145	15.5	328	4146	17800
vetilleo con sulfuros de Pb y Zn	101.70	102.50	0.80	0.060	36	1956	749	799
vetilleo con sulfuros de Pb y Zn	102.50	103.30	0.80	0.015	61.9	4774	1881	570
vetilleo con sulfuros de Pb y Zn	103.30	104.40	1.10	0.195	14.7	680	566	738

<b>ST-07-07 Bearing 145 Dip -45 Length 87.9m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Quartz veining with diss specul	10.15	10.65	0.50	0.010	3.6	57	85	2069
Quartz veining with diss specul	10.65	11.50	0.85	<0.005	0.9	4	112	534
Quartz veining with diss specul	11.50	12.15	0.65	0.005	<0.1	14	82	458
Wh qtz vein	51.10	51.45	0.35	0.230	32.8	697	221	124
Quartz veining with stockwork	63.70	64.50	0.80	<0.005	<0.1	65	77	739
Quartz veining with stockwork	64.50	65.50	1.00	0.065	<0.1	<1	63	801
Quartz veining with stockwork	65.50	66.55	1.05	0.085	<0.1	<1	38	583
Quartz veining with stockwork	66.55	67.65	1.10	0.030	1.5	<1	76	824
Quartz veining with stockwork	67.65	68.75	1.10	0.015	0.7	<1	44	244
Quartz veining with stockwork	68.75	69.95	1.20	0.020	0.8	<1	22	163
Quartz veining with stockwork	75.00	76.40	1.40	0.010	3.6	17	71	720
Quartz veining with stockwork	79.55	80.55	1.00	0.036	13.9	<1	120	256
Santiago vein	80.55	81.50	0.95	0.050	1.1	<1	96	623
Santiago vein	81.50	81.95	0.45	0.010	3	<1	29	736

<b>ST-07-06 Bearing 195 Dip -50 Length 62.45m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
White quartz veining with pyrite	24.65	25.50	0.85	0.055	26.1	142	240	1377
Quartz vein w/sulfides	25.50	26.35	0.85	0.020	1.6	34	77	389
Strong diss pyrite	33.20	33.90	0.70	0.115	68.2	667	2820	786
Strong diss pyrite	33.90	35.00	1.10	0.020	2.5	92	133	844
Strong diss pyrite	35.00	36.30	1.30	0.010	3.5	10	55	315
Strong diss pyrite	36.30	37.60	1.30	0.015	1.8	96	46	173
Strong diss pyrite	37.60	38.75	1.15	0.020	28.8	30	162	400
Quartz vein	38.75	39.85	1.10	<0.005	0.6	<1	47	252
Diss py	39.85	40.95	1.10	0.010	6.9	630	133	316
Diss py	45.20	45.70	0.50	0.015	2.8	494	155	6976
Strong diss pyrite	47.40	48.10	0.70	0.020	<0.1	8	38	468
Strong diss pyrite	48.10	48.80	0.70	<0.005	0.7	7	41	326
Strong diss pyrite	48.80	50.00	1.20	0.015	5	165	81	311
Strong diss pyrite	50.00	50.90	0.90	0.005	1.5	2	84	332
Santiago vein	50.90	51.80	0.90	<0.005	<0.1	<1	111	333
Santiago vein	51.80	52.45	0.65	0.045	1.3	<1	64	308

Santiago vein	52.45	53.10	0.65	0.060	25.1	1100	71	335
Santiago vein	53.10	53.90	0.80	0.025	5.4	98	63	332
Santiago vein	53.90	54.80	0.90	0.090	21.8	47	209	298
White quartz veining with pyrite	54.80	55.80	1.00	0.068	9.6	20	156	347

<b>ST-07-05 Bearing 110 Dip -45 Length 196m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
zona de ramaleo con hilos de p	35.35	35.90	0.55	0.015	3.8	32	107	559
veta con sulfuros	35.90	36.85	0.95	1.670	273.3	375	1247	923
zona abundante con pirita	36.85	37.70	0.85	0.091	70.6	524	404	657
zona abundante con pirita	37.70	38.60	0.90	0.060	11.7	133	236	210
zona abundante con pirita	38.60	39.45	0.85	0.020	6.3	64	141	246
zona de ramaleo con pirita	39.45	40.00	0.55	0.020	2.5	24	103	225
zona de ramaleo con pirita	40.00	40.95	0.95	0.020	4.7	18	129	202
veta Santiago	40.95	42.00	1.05	0.270	41.8	650	625	1724
zona abundante con pirita	42.00	42.55	0.55	0.064	21.5	254	301	406
Diss cpy	141.75	142.60	0.85	0.015	19.3	4298	111	1348
Diss cpy	142.60	143.60	1.00	0.115	19.2	3310	141	1006
zonz abundante de prita	143.60	144.15	0.55	0.159	24.2	1443	173	935
zona de falla	144.15	144.70	0.55	0.170	24.2	603	179	5455
zona abundante con pirita	144.70	145.25	0.55	0.130	6.6	76	146	1239
zona abundante con pirita	153.70	154.20	0.50	0.050	5	31	120	509
veta Santiago	154.20	154.75	0.55	0.195	14.9	51	92	1164
zona abundante con pirita	154.75	155.25	0.50	0.030	2.8	23	127	2052
vetilla con sulfuros	183.60	184.00	0.40	0.305	47.6	1706	7636	35200
zona de vetilleo	187.30	187.80	0.50	2.185	21.2	289	2133	2423

<b>ST-07-04 Bearing 158 Dip -45 Length 100.9m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
zona de vetilleo	24.65	24.90	0.25	0.398	99.3	442	723	916
zona de vetilleo	26.80	27.10	0.30	0.141	22.3	706	713	840
vetila con sulfuros	63.00	63.75	0.75	0.039	10.5	466	177	412
zona de ramaleo	63.75	64.50	0.75	0.020	5.9	37	151	599
veta Santiago	75.30	75.73	0.43	0.248	8.6	62	210	794
veta Santiago	75.75	76.50	0.75	0.484	73.8	632	753	2610
veta Santiago	76.50	77.50	1.00	0.148	40.7	581	302	638
veta Santiago	77.50	78.40	0.90	0.085	32.7	653	869	2416
veta Santiago	78.40	79.40	1.00	0.020	13.1	390	142	480
veta Santiago	79.40	80.55	1.15	0.199	54.1	752	399	2383
zona de vetilleo	91.25	91.95	0.70	0.300	26.7	1669	247	1768

<b>ST-07-03 Bearing 128 Dip -45 Length 80.9m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Vetilleo con abundante pirita	15.00	15.90	0.90	0.210	38.2	3362	339	182
vetilla con sulfuros	43.85	44.25	0.40	0.617	17.7	319	834	3231
zona de falla	62.40	63.05	0.65	0.050	5.5	449	170	1384
zona de falla	63.05	63.85	0.80	0.043	3.2	273	121	886
zona silificada	63.85	64.75	0.90	0.335	25	389	363	1018
zona silificada	64.75	65.65	0.90	0.109	33.4	1784	183	780
veta Santiago	72.15	72.75	0.60	0.105	38.2	1418	783	2996
veta Santiago	72.75	73.40	0.65	0.057	11.3	192	632	1465
zona de vetilleo	77.35	77.85	0.50	0.619	24.8	201	1451	10100

<b>ST-07-02 Bearing 180 Dip -45 Length 200.05m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Strong silicification + diss pyrite	46.20	47.20	1.00	0.085	11.2	21	1082	2418
	47.20	48.20	1.00	0.325	38.2	417	4960	6845
	48.20	49.20	1.00	0.03	4.9	20	204	518
Strong silicification + diss pyrite	65.60	66.50	0.90	<0.005	8.3	79	4810	6612
Strong silicification + diss pyrite	66.50	67.50	1.00	0.015	2.3	10	64	261
Strong silicification + diss pyrite	67.50	68.50	1.00	0.015	2.3	10	85	647
Strong silicification + diss pyrite	68.50	69.55	1.05	<0.005	1	53	192	2121
Strong silicification + diss pyrite	69.55	70.55	1.00	0.025	4.6	10	84	365
Strong silicification + diss pyrite	70.55	71.55	1.00	0.01	3.5	7	126	326
Strong silicification + diss pyrite	71.55	72.60	1.05	0.005	2	7	43	440
Strong silicification + diss pyrite	72.60	73.60	1.00	<0.005	2	6	36	132
Strong silicification + diss pyrite	73.60	74.60	1.00	<0.005	1.4	36	42	145

Strong silicification + diss pyrite	74.60	75.65	1.05	<0.005	<0.1	17	41	221
Strong silicification + diss pyrite	79.25	80.25	1.00	<0.005	2.1	6	56	1556
Strong silicification + diss pyrite	80.25	81.25	1.00	0.025	3.8	293	526	2297
Wh quartz vein w/sulfides Pb-Zn	120.80	121.10	0.30	0.09	59.1	2652	14100	37800
Strong silicification + diss pyrite	136.00	137.00	1.00	0.015	17.3	167	4494	351
Strong silicification + diss pyrite	137.00	138.00	1.00	<0.005	1.3	19	88	261
Strong silicification + diss pyrite	138.00	139.00	1.00	<0.005	1.4	21	135	196
Strong silicification + diss pyrite	139.00	140.00	1.00	0.015	3.2	6	143	107
Strong silicification + diss pyrite	140.00	141.00	1.00	0.01	0.1	3	72	164
Strong silicification + diss pyrite	141.00	142.00	1.00	0.015	1.5	6	108	728
Strong silicification + diss pyrite	142.00	143.00	1.00	0.01	1.3	6	94	195
Strong silicification + diss pyrite	143.00	144.00	1.00	0.040	6.5	7	115	455
Strong silicification + diss pyrite	144.00	145.00	1.00	0.045	6.4	8	79	234
Strong silicification + diss pyrite	145.00	146.00	1.00	0.060	8	13	170	194
Strong silicification + diss pyrite	146.00	146.65	0.65	<0.005	5.3	10	75	173
Strong silicification + diss pyrite	152.20	153.20	1.00	0.015	6.3	14	56	138
Strong silicification + diss pyrite	153.20	154.20	1.00	<0.005	1.4	6	44	159
Strong silicification + diss pyrite	154.20	154.85	0.65	0.04	12.1	74	154	321

<b>ST-07-01 Bearing 180 Dip -50 Length 309.05m</b>								
Description	From (Metres)	To (Metres)	Down Hole Lengths (metres)	Au (g/t)	Ag (g/t)	Cu (g/t)	Pb (g/t)	Zn (g/t)
Wh qtz veinlet w/strong sulfides	51.00	51.25	0.25	7.260	37	108	>10000	>10000
Qtz veinlet	55.45	56.45	1.00	0.040	55.9	9940	1038	402
Quartz vein with strong pyrite	114.65	115.40	0.75	0.120	5.8	37	154	1380
Quartz veining w/pyrite	118.45	118.85	0.40	0.025	2.7	11	101	380
Veinlet w/moderate pyrite	120.75	121.35	0.60	0.095	6.8	184	358	579
Vein w/ strong specularite	133.35	133.75	0.40	0.171	2.8	2	105	260
Veinlet w/ pyrite and Pb-Zn	134.05	134.35	0.30	0.04	5.3	373	2720	>10000
Veinlet w/pyrite and Pb-Zn	134.35	135.55	1.20	0.155	4.9	493	1132	>10000
Quartz veining w/moderate pyrite	261.40	261.75	0.35	0.03	0.8	55	26	318
Strong silicification-pyrite	261.75	262.80	1.05	<0.005	<0.1	5	35	420
Strong silicification-pyrite	262.80	263.95	1.15	<0.005	<0.1	7	37	240
Santiago vein	263.95	264.55	0.60	0.065	1.2	10	86	230
Santiago vein	264.53	265.15	0.62	0.015	1.5	25	73	148
Santiago vein	265.15	266.30	1.15	0.01	<0.1	3	43	110
Strong silicification-pyrite	277.25	277.85	0.60	<0.005	<0.1	1	118	51
	277.85	278.45	0.60	0.015	5.1	6	2645	46
	278.45	278.95	0.50	0.035	2.7	6	119	37