



NI 43-101 compliant inferred tailings resource calculation

	Tonnage	Grade (Ag)	Grade (Au)	Ounces (Ag)	Ounces (Au)
Oxide Tailings	2,091,074	95 g/t	0.53 g/t	6,420,538	35,624
Sulfide Tailings	2,900,000	37.78 g/t	0.34 g/t	3,522,554	31,701
Total	4,991,074			9,943,092	67,325

* Taken from Wardrop Engineering's March 2006 report: *form-43-101F1 Technical Report: Tailings Retreatment Options*